

*Thank you for your comments on Criteria AC132.*

Donald Portfolio  
PRI Construction Materials Technologies  
813-621-5777  
dportfolio@pricmt.com

*Comments:*

For the evaluation of accelerated weathering, ASTM D 256B, impact resistance, is used to determine the effect of accelerated weathering on the plastic. Suggest that you also include as an alternate ASTM D 638 for tensile, as in some cases, it is difficult or impossible to evaluate impact due to the flexibility of the plastic used to manufacture vents. Suggest a 10 percent variance in properties which is in line with Miami-Dade requirements.