



ICC Evaluation Service, Inc.
Birmingham Regional Office
900 Montclair Road, Suite A
Birmingham, AL 35213
tel: 205.599.9800
fax: 205.599.9850
www.icc-es.org

February 1, 2010

TO: PARTIES INTERESTED IN EVALUATION REPORTS ON ROOF UNDERLAYMENTS

SUBJECT: Proposed Revisions to the Acceptance Criteria for Roof Underlayments, Subject AC188-0210-R1 (WM/JV)

Dear Madam or Sir:

The revisions proposed to the subject acceptance criteria, as presented in the enclosed criteria draft, are being posted on the ICC-ES web site to allow for public comment. The revisions include:

1. Updating AC188 to the 2009 I-Codes, and deleting references to the UBC.
2. Updating Section 1.3 (Referenced Documents) to reference the current editions of standards. Overall, changes to the section may be explained as follows:
 - The updated versions of ASTM D 226, ASTM D 4869 and ASTM E108 are mandated by the 2009 *International Building Code*[®] and the 2009 *International Residential Code*[®].
 - ASTM D 412, ASTM D 828, ASTM D 1682 and ASTM D 3018 are not referenced by the 2009 IBC or IRC.
 - References to ASTM D 412 and ASTM D 3018 have been updated to the current editions. Industry input is requested on the effect of changing the referenced editions of these two ASTM standards.
 - ASTM D 828 has been withdrawn by ASTM with no replacement. Industry input is requested as to the appropriate test standard (if needed) to use in place of ASTM D 828.
 - ASTM D 1682 has been replaced by ASTM D 5034 and ASTM D 5035. Industry input is requested on the effect in AC188 of replacing ASTM D 1682 with ASTM D 5034 and ASTM D 5035 in AC188.

You are cordially invited to submit written comments, within 30 days of the date of this letter. Please use the comment form on the web site attaching any letters to the form. An explanation of the alternate criteria process can be found on our web site at http://www.icc-es.org/Criteria_Development/alternative_criteria_process.shtml.


All comments received in the 30-day comment period will be considered in preparing revisions to the criteria that may be considered at a future Evaluation Committee meeting. Comments received will be posted on the web site shortly after the close of the comment period.

Your cooperation is requested in forwarding to the Los Angeles business/regional office all material directed to the Evaluation Committee. Parties interested in the deliberations of the committee should refrain from communicating, whether in writing or verbally, with committee members. The committee reserves the right to refuse communications that do not comply with this request.

Newly approved acceptance criteria may involve test methods or test protocols that are not currently included in the scope of testing services offered by accredited testing laboratories. As noted in the ICC-ES Rules of Procedure for Evaluation Reports, the scope of the laboratory's accreditation must include the type of testing that is to be reported to ICC-ES. We encourage accredited laboratories to expand their scopes of accreditation to include testing under newly approved acceptance criteria. Please note that testing laboratories must be accredited by the International Accreditation Service (IAS) or by another accreditation body that is a signatory to the International Laboratory Accreditation Cooperation Mutual Recognition Arrangement. For further information, please contact IAS at (562) 699-0541, extension 3309, or send an e-mail to pmccullen@iasonline.org.

Please submit all comments using the form on the web site. Attach any letters to the comment form. If you have any questions (not comments), please contact the undersigned at (800) 423-6587, extension 5686, or Jose Valencia, Staff Architect, at extension 5693. You may also reach us by e-mail at es@icc-es.org.

Yours very truly,



Woods McRoy, P.E.
Senior Staff Engineer

WFM/raf

Enclosure

cc: Evaluation Committee

PROPOSED REVISIONS TO THE ACCEPTANCE CRITERIA FOR ROOF UNDERLAYMENTS

AC188

Proposed February 2010

Previously approved July 2007, February 2003, November 2001

PREFACE

Evaluation reports issued by ICC Evaluation Service, Inc. (ICC-ES), are based upon performance features of the International family of codes and other widely adopted code families, including the Uniform Codes, the BOCA National Codes, and the SBCCI Standard Codes. Section 104.11 of the *International Building Code*® reads as follows:

The provisions of this code are not intended to prevent the installation of any materials or to prohibit any design or method of construction not specifically prescribed by this code, provided that any such alternative has been approved. An alternative material, design or method of construction shall be approved where the building official finds that the proposed design is satisfactory and complies with the intent of the provisions of this code, and that the material, method or work offered is, for the purpose intended, at least the equivalent of that prescribed in this code in quality, strength, effectiveness, fire resistance, durability and safety.

Similar provisions are contained in the Uniform Codes, the National Codes, and the Standard Codes.

ICC-ES may consider alternate criteria, provided the report applicant submits valid data demonstrating that the alternate criteria are at least equivalent to the criteria proposed in this document, and otherwise meet the applicable performance requirements of the codes. Notwithstanding that a product, material, or type or method of construction meets the requirements of the criteria proposed in this document, or that it can be demonstrated that valid alternate criteria are equivalent to the criteria in this document and otherwise meet the applicable performance requirements of the codes, ICC-ES retains the right to refuse to issue or renew an evaluation report, if the product, material, or type or method of construction is such that either unusual care with its installation or use must be exercised for satisfactory performance, or malfunctioning is apt to cause unreasonable property damage or personal injury or sickness relative to the benefits to be achieved by the use of the product, material, or type or method of construction.

Acceptance criteria are developed for use solely by ICC-ES for purpose of issuing ICC-ES evaluation reports.

PROPOSED REVISIONS TO THE ACCEPTANCE CRITERIA FOR ROOF UNDERLAYMENTS

1.0 INTRODUCTION

1.1 Purpose: The purpose of this acceptance criteria is to establish requirements for recognition of roof underlayments in an ICC-ES Evaluation Service, Inc. (ICC-ES), evaluation report under the ~~2006~~ **2009** *International Building Code*[®] (IBC), ~~and the 2006~~ **2009** *International Residential Code*[™] (IRC) ~~and the 1997~~ *Uniform Building Code*[™] (UBC). Bases of recognition are IBC Section 104.11, ~~and~~ IRC Section R104.11 ~~and UBC Section 1402.8.~~

The reason for development of this criteria is to provide guidelines for the evaluation of alternative roof underlayments that are not addressed in the code.

1.2 Scope: This criteria is limited to membrane materials used as roofing underlayment, either self-adhering or mechanically attached, and installed over solid sheathing. The membrane materials are alternatives to the ASTM D 226, Type I and Type II, underlayments specified in Chapter 15 of the IBC and Chapter 9 of the IRC, ~~and to the Type 15 and Type 30 underlayments specified in Chapter 15 of the UBC.~~

The roof underlayments are limited to buildings permitted to have nonclassified roofing in accordance with IBC Section 1505.5, ~~and nonrated roofing in accordance with UBC Section 1504.3,~~ unless successful fire tests are conducted in accordance with Section 3.3 of this criteria.

1.3 Referenced Documents:

1.3.1 ~~2006~~ **2009** *International Building Code*[®] (IBC), International Code Council.

1.3.2 ~~2006~~ **2009** *International Residential Code*[®] (IRC), International Code Council.

~~**1.3.3** 1997 *Uniform Building Code*[™] (UBC).~~

~~**1.3.4** 1997 UBC Standard 15-2, Test Standard for Determining Fire Retardancy of Roof Assemblies.~~

~~**1.3.3** **1.3.5** ICC-ES Acceptance Criteria for Roof Underlayment for Use in Severe Climate Areas (AC48).~~

~~**1.3.4** **1.3.6** ASTM D 226-97a **06**, Specification for Asphalt-Saturated Organic Felt Used in Roofing and Waterproofing, ASTM International.~~

~~**1.3.5** **1.3.7** ASTM D 412-98a **06ae2**, Test Method for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers-Tension, ASTM International.~~

~~**1.3.8** ASTM D 828-97, Test Method for Tensile Properties of Paper and Paperboard Using Constant Rate-of-Elongation Apparatus, ASTM International.~~

~~**1.3.9** ASTM D 1682-64 (1975), Test Method for Breaking Load and Elongation of Textile Fabrics, ASTM International.~~

~~**1.3.6** **1.3.10** ASTM D 1970-01, Specification for Self-Adhering Polymer Modified Bituminous Sheet Materials, ASTM International.~~

~~**1.3.7** **1.3.11** ASTM D 3018-90 **09** (1994)⁴, Specification for Class A Asphalt Shingles Surfaced with Mineral Granules, ASTM International.~~

~~**1.3.8** **1.3.12** ASTM D 4869-04 **05e01**, Specification for Asphalt-Saturated (Organic Felt)~~

Underlayment Used in Steep Slope Roofing, ASTM International.

~~**1.3.9** **ASTM D 5034-09, Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test).**~~

~~**1.3.10** **ASTM D 5035-06(2008)e1, Standard Test Method for Breaking Force and Elongation of Textile Fabrics (Strip Method).**~~

~~**1.3.11** **1.3.13** ASTM E 108-04 **07a**, Test Methods for Fire Tests of Roof Coverings, ASTM International.~~

~~**1.3.12** **1.3.14** UL 790-04, Tests for Fire Resistance of Roof Covering Materials—with Revisions through July, 1998.~~

2.0 BASIC INFORMATION AND REPORTS OF TESTS

2.1 Product Description: Description of the underlayment sheet materials, and of the manufacturing process, shall be submitted.

2.2 Installation Instructions: Installation instructions shall be submitted.

2.3 Packaging and Identification: Description of the method of packaging and identification of the underlayment shall be submitted. Product labeling shall include the evaluation report number and the name or logo of the inspection agency.

2.4 Testing Laboratories, Reports of Tests and Product Sampling:

2.4.1 Testing laboratories shall comply with Section 2.0 of the ICC-ES Acceptance Criteria for Test Reports (AC85) and Section 4.2 of the ICC-ES Rules of Procedure for Evaluation Reports.

2.4.2 Test reports shall comply with AC85.

2.4.3 Sampling of the underlayment for tests under this criteria shall comply with Section 3.1 of AC85.

2.4.4 Unless otherwise noted in this criteria, specimen sizes, quantities, and test configurations are as noted in the referenced standards.

3.0 REQUIRED DATA

3.1 For installation over solid sheathing, reports of tests showing conformance of the materials to the requirements of Table 1 shall be submitted.

3.2 Reports of tests shall be submitted to demonstrate that the finished product does not crack, and is not so sticky as to cause tearing or other damage, upon being unrolled at temperatures between 50°F and 140°F (10°C and 60°C).

3.3 For recognition of installation on buildings other than those permitted by the applicable code to have nonrated **classified** roof coverings, reports of roof classification tests conducted in accordance with ASTM E 108 or UL 790 (IBC, IRC) or UBC Standard 15-2 (UBC) shall be submitted.

Two Class A intermittent flame and four Class A burning brand decks shall be tested. The assemblies shall consist of a single layer of the subject underlayment installed over solid or spaced sheathing, depending on the recognition sought, and a roof covering of three-tab

PROPOSED REVISIONS TO THE ACCEPTANCE CRITERIA FOR ROOF UNDERLAYMENTS

asphalt shingles complying with ASTM D 3018 and having a maximum installed weight of 190 pounds per 100 square feet (9.28 kg/m²). Tests shall be conducted at a slope of 5:12 (41.67%). Test decks shall be constructed with nominal 3/8-inch-thick (9.5 mm) plywood.

Based on successful completion of the tests, the evaluation report on the underlayment will state that the underlayment is permitted to be used as an alternate to the underlayment specified in the applicable code for roof coverings of brick, masonry, slate, clay or concrete roof tile, exposed concrete roof deck, ferrous or copper shingles or sheets, and metal sheets and shingles and nonfire-retardant-treated wood. The noted roof coverings are permitted to be used in IBC Section 1505.2, IRC Section R902.1 and UBC Section 1504.2, wherever a Class A, B or C roof covering assembly is required.

4.0 QUALITY CONTROL

4.1 The products shall be manufactured under an approved quality control program with inspections by an inspection agency accredited by the International Accreditation Service (IAS) or otherwise acceptable to ICC-ES.

4.2 Quality documentation complying with the ICC-ES Acceptance Criteria for Quality Documentation (AC10) shall be submitted for the roof underlayment.

5.0 EVALUATION REPORT RECOGNITION

5.1 Self-adhering underlayments are limited to installation on the substrates qualified through compliance with the adhesion in peel requirements of Table 1. The evaluation report will list the recognized substrates.

5.2 Installation of underlayments is limited to roof slopes of 2:12 (16.67%) and greater and installations where the roof covering does not involve hot asphalt or coal tar pitch.

5.3 Underlayments recognized through compliance with this criteria are limited to use with roof coverings that are mechanically fastened through the underlayment to the sheathing or rafters.

5.4 Attic ventilation in accordance with the applicable code is required since vapor permeance of the underlayments is not addressed by this criteria. ■

TABLE 1—REQUIREMENTS FOR INSTALLATION OVER SOLID SHEATHING¹

DESCRIPTION	TEST METHOD	REQUIREMENTS
Pliability	ASTM D 226	No cracking when bent 90° at a uniform speed over a rounded corner of 1/2-inch radius
Accelerated aging	AC48, Section 4.7	No visible damage such as chipping or cracking. No delamination. Additional testing for tensile strength and adhesion in peel
Ultraviolet exposure	AC48, Section 4.8	No visible damage such as chipping or cracking. No delamination. Additional testing for tensile strength and adhesion in peel
Tensile strength ² (machine and cross-machine direction) - Control specimens - After accelerated aging - After UV exposure	AC48, Sections 4.1, 4.7, and 4.8	ASTM D 828 or D 412: minimum 20 lbf/in-width ASTM D4682 <u>5034 and ASTM D 5035</u> : minimum 75 lbf ASTM D 1970: minimum 25 lbf/in-width
Adhesion in peel (adhered membranes only) ³ - Control specimens - After 7-day water immersion - After accelerated aging - After UV exposure	AC48, Sections 4.5, 4.7, and 4.8	Conditioned specimens must exceed 75% of the value determined for the control specimens, for each substrate
Liquid water transmission	ASTM D 4869	Shall meet the “Pass” requirements of Section 8.3.5 of ASTM D 4869
Cycling and elongation (adhered membranes only)	AC48, Section 4.6	No cracking of the material or bond failure between the product and the plywood substrate

For **SI**: 1 inch = 25.4 mm, 1 lbf = 4.45N, 1 lbf/inch width = 0.175N/m.

¹All specimens shall be conditioned in accordance with the referenced standard or acceptance criteria, unless otherwise noted in this acceptance criteria.

²Requirements apply to both the machine and cross-machine direction for each exposure condition. For self-adhering materials, specimens with seam treatment representative of installed conditions must be evaluated for tensile strength. For laminated membranes, failure in tensile strength is defined as the maximum load occurring upon or prior to the first occurrence of delamination of the composite, or tearing or ultimate failure of any individual component of the laminate.

³Adhered membranes shall be tested for adhesion-in-peel on each substrate for which recognition is sought. All exposure conditions must be evaluated for each substrate.