



Joint Evaluation Report

ICC-ES | (800) 423-6587 | (562) 699-0543 | www.icc-es.org

ESR-1262

Reissued 01/2018

This report is subject to renewal 01/2019.

DIVISION: 06 00 00—DIVISION NAME

SECTION: 06 17 33—SECTION NAME

REPORT HOLDER:

EACOM TIMBER CORPORATION

**1195 PEOPLES ROAD
SAULT STE. MARIE, ONTARIO P6C 3W7
CANADA**

EVALUATION SUBJECT:

POWER JOIST® PJI-40, PJI-60, PJI-80 AND PJI-90 I-JOISTS



Look for the trusted marks of Conformity!

“2014 Recipient of Prestigious Western States Seismic Policy Council (WSSPC) Award in Excellence”



A Subsidiary of

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Joint Evaluation Report

ESR-1262

Reissued January 2018

Revised February 2018

This report is subject to renewal January 2019.

www.icc-es.org | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES
Section: 06 17 33—Wood I-joists

REPORT HOLDER:

EACOM TIMBER CORPORATION
1195 PEOPLES ROAD
SAULT STE. MARIE, ONTARIO P6C 3W7
CANADA
(705) 254-7597
www.eacom.ca

ADDITIONAL LISTEES:

GEORGIA-PACIFIC, LLC
133 PEACHTREE STREET N.E.
ATLANTA, GEORGIA 30303
(404) 652-4000

BLUELINX CORPORATION
4300 WILDWOOD PARKWAY
ATLANTA, GEORGIA 30339
(770) 953-7000

EVALUATION SUBJECT:

POWER JOIST® PJI-40, PJI-60, PJI-80 AND PJI-90 I-JOISTS

1.0 EVALUATION SCOPE

1.1 Compliance with the following codes:

- 2012, 2009 and 2006 *International Building Code*® (IBC)
- 2012, 2009 and 2006 *International Residential Code*® (IRC)
- 2013 *Abu Dhabi International Building Code* (ADIBC)†

†The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

Properties evaluated:

- Structural
- Fire resistance

1.2 Evaluation to the following green code(s) and/or standards:

- 2016 and California Green Building Standards Code (CALGreen), Title 24, Part 11
- 2015, 2012 and 2008 ICC 700 *National Green Building Standard*™ (ICC 700-2015, ICC 700-2012 and ICC 700-2008)

Attributes verified:

See Section 3.1.

2.0 USES

Power Joist® I-joists are used as rim joists, roof rafters and joists in roof and floor/ceiling assemblies for single and multiple-span conditions in buildings of Type V construction.

3.0 DESCRIPTION

3.1 General:

Power Joist® I-joists are structural elements manufactured using finger-jointed, solid-sawn wood flanges and wood structural panel webs bonded together with an exterior-grade adhesive forming an “I” cross-sectional shape. The Power Joist I-joists are manufactured to meet the performance standard entitled “PRI-400 Performance Standard for APA EWS I-joists,” recognized in [ESR-1405](#), and the EACOM Timber Corporation quality control manual. The company names and associated product trade names for the Power Joist® and private-label I-joists are as follows:

COMPANY OR LISTEE	PRODUCT TRADE NAME AND SERIES
EACOM Timber Corporation	PJI 40, 60, 80 and 90
Georgia-Pacific, LLC	WI 40, 60, 80 and 90
BlueLinx Corporation	BLI 40, 60, 80 and 90

All PJI I-joists, regardless of the private-label mark, are identified as described in Section 7.0 of this report.

The attributes of the wood I-joists have been verified as conforming to the requirements of (i) 2016 and CALGreen Sections A4.404.3 for efficient framing techniques; (ii) ICC 700-2015 and ICC 700-2012 Section 608.1(2), 11.608.1(2) and 12(A).608.1 for resource-efficient materials; and (iii) ICC 700-2008 Section 607.1(2) for resource-efficient materials. Note that decisions on compliance for those areas rest with the user of this report. The user is advised of the project-specific provisions that may be contingent upon meeting specific conditions, and the verification of those conditions is outside the scope of this report. These codes or standards often provide supplemental information as guidance.

3.2 Material Specifications:

3.2.1 Flanges: Power Joist® I-joists are fabricated from solid-sawn SPF, Grade 1650 MSR for PJI-40, Grade 2100 MSR for PJI-60 and PJI-80 flanges, and Grade 2400 MSR for PJI-90 flanges [nominal size of 2 inches by 3 inches

(51 by 76 mm) for PJI-40 and PJI-60, and 2 inches by 4 inches (51 by 102 mm) for PJI-80 and PJI-90].

Power Joist® I-joists have a constant depth that varies from 9½ to 16 inches (241 to 406 mm) for the PJI-40 and PJI-60, and from 11⅞ to 24 inches (302 to 910 mm) for the PJI-80 and PJI-90. The I-joists are produced in lengths from 12 to 64 feet (3657 to 19 507 mm).

3.2.2 Web: Webs consist of ⅜-inch-thick or ⅞-inch-thick (9.5 mm or 11.1 mm), oriented strand board (OSB), which meets the requirements of the United States Department of Commerce Product Standard PS-2 for Structural 1, Exposure 1, rated panels.

3.2.3 Adhesive: Adhesives are exterior type complying with ASTM D2559 and as specified in the quality control manual that contains Power Joist® manufacturing standards. The adhesives have also been tested in accordance with ASTM D7247.

4.0 DESIGN AND INSTALLATION

4.1 General:

Installation of Power Joist® I-joists must comply with this report and the manufacturer's published installation instructions. The manufacturer's published installation instructions must be available at the jobsite at all times during installation.

4.2 Design Values:

Design values listed in this report for Power Joist® I-joists are limited to I-joists installed in covered, dry conditions of use. Dry conditions of use are environmental conditions represented by sawn lumber in which the moisture content is less than 16 percent.

See Tables 1A, 1B, and 2 of this report for allowable design values and span/load values of Power Joist® I-joists. See Figure 1 of this report for a typical cross section of a Power Joist® I-joist, showing flange and web dimensions. See Table 3 of this report for allowable web hole sizes and locations.

With the exception of reference design reactions, reference design values for Power Joist® I-joists must be adjusted using the appropriate adjustment factors as specified in *American Forest and Paper Association, National Design Standard for Wood Construction* with the Supplement *Design Values for Wood Construction* (AF&PA NDS). Reference design reactions, corresponding to various load duration factors, are given in Table 1B.

4.3 Deflection:

Maximum allowable deflection of Power Joist® I-joists under design loads must not exceed the maximum allowable deflections specified in Section 1604.3 of the IBC, and Section R301.7 of the IRC. The method to calculate the deflection is as follows:

Calculated deflection of the joists under design load, utilizing the deflection formulas listed below:

$$\Delta = 5w\ell^4/(384 EI) + w\ell^2/K \text{ for uniformly distributed loads}$$

$$\Delta = P\ell^3/(48 EI) + 2P\ell / K \text{ for simple span with a concentrated load at mid-span}$$

where:

P = Concentrated load (lbf)

w = Uniform loads (lbf/in.)

EI = Bending stiffness (in.² - lbf)

ℓ = Span (inches) between centers of supports.

K = Coefficient of shear deflection (lbf) (see Table 1A of this report)

Δ = Calculated deflection (in.)

4.4 Shear Load:

Vertical shear load calculations must include all loads resisted by the Power Joist® I-joists between the faces of the supports.

4.5 Lateral Support:

The compression flange of Power Joist® I-joists must be provided with continuous lateral support. Sheathing fastened in accordance with the applicable code may be used to provide this lateral support at the top flange. Continuous bracing must also be provided to support the bottom flange in areas of negative moment over interior supports and at cantilevers. Additionally, the ends of Power Joist® I-joists must be provided with lateral support to resist rollover at bearing locations. This lateral support may be provided by either end blocking, rim joist, or cross bridging and must be installed consistent with the lateral stability presumed in the design calculations.

4.6 Bottom Flange Loads:

Concentrated loads imposed on the bottom flange of the joists have not been evaluated and are outside the scope of this report.

4.7 End Bearing:

End bearing length must be a minimum 1¾ inches (44 mm) for simple spans; for multiple span joists, intermediate bearing length must be a minimum 3½ inches (89 mm). Power Joist® I-joist bearing lengths must be in accordance with Table 1B of this report.

4.8 Repetitive-member Use:

The repetitive-member use factors applicable to the moment capacities listed in Table 1A of this report are limited to 1.0.

4.9 Holes in I-joist Web:

Table 3 of this report specifies allowable sizes and locations of round holes in the I-joist webs.

4.10 Member Spans:

I-joist spans may be determined in accordance with Table 2 of this report. Vertical shear calculations must include all loads within the span from face to face of supports.

4.11 Fasteners:

Fastener design values must be in accordance with the applicable code. Fastener spacings must comply with the minimum spacing requirements prescribed by the code for nails installed in sawn lumber having a minimum specific gravity of 0.42 such as for spruce-pine-fir. Fastening must be accomplished in a manner that will not cause splitting in the I-joist flanges.

4.12 Web Stiffeners:

Web stiffener requirements for reactions and concentrated loads are as shown in Table 1B and Figure 3 of this report.

4.13 Fire-resistance-rated Construction:

The Power Joist I-joists described in this report may be used as described in Section 4.2.2 of [ESR-1405](#). Evaluation of the use of Power Joist I-joists as a component of other fire-resistance-rated roof or floor assemblies is outside the scope of this report.

5.0 CONDITIONS OF USE

The Power Joist® I-Joists described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 Installation must comply with this report, the manufacturer’s published installation instructions and the applicable code. If there is a conflict between the installation instructions and this report, this report governs.
- 5.2 Design calculations and details for specific applications demonstrating that Power Joist® I-joists comply with this report must be submitted to the code official. The design calculations and details for specific applications must be prepared by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.

Calculations must indicate the following:

- Load duration factor used in accordance with AF&PA NDS.
- Required design capacities of the I-joists under design loads.
- Allowable design capacities of the Power Joist® I-joists.
- Allowable deflection of the Power Joist® I-joists consistent with this report.


- 5.3 Cutting and notching of Power Joist® I-joist flanges is not permitted, except for cutting to proper length for installation.
- 5.4 The use of pressure-treated Power Joist® I-joists, or portions thereof, is outside the scope of this report.
- 5.5 Evaluation of the use of Power Joist® I-joists as a component of fire-resistance-rated construction is as noted in Section 4.13 of this report.
- 5.6 Web opening sizes and locations within Power Joist® I-joists must be limited to the criteria in Table 3 of this report. Web opening conditions not covered in Table 3 of this report have not been evaluated and are outside the scope of this report.
- 5.7 Power Joist® I-joists are produced in Sault St. Marie, Ontario, Canada, under a quality control program with inspections by ICC Evaluation Service, LLC.

6.0 EVIDENCE SUBMITTED

Data in accordance with the ICC-ES Acceptance Criteria for Prefabricated Wood I-joists (AC14), dated October 2017.

7.0 IDENTIFICATION

Each I-Joist must be marked with the product trade name; the joist series; the production date; the evaluation report number (ESR-1262); and the name or trademark of the inspection agency (APA – The Engineered Wood Association).



I-Joist Series	Flange Grade	Flange Size (depth x width) (inches)	Web Thickness (inches)	Range of I-Joist Depths (inches)
PJI-40	1.5E	1.5 x 2.5	³ / ₈	9 ¹ / ₂ to 16
PJI-60	1.8E	1.5 x 2.5	³ / ₈	9 ¹ / ₂ to 16
PJI-80	1.8E	1.5 x 3.5	³ / ₈	11 ⁷ / ₈ to 16
			⁷ / ₁₆	18 to 24
PJI-90	2.0E	1.5 x 3.5	⁷ / ₁₆	11 ⁷ / ₈ to 24

For SI: 1 inch = 25.4 mm.

FIGURE 1—POWER JOIST® I-JOIST DIMENSIONS

TABLE 1A—REFERENCE DESIGN VALUES^{1,2,3}

JOIST SERIES	DEPTH (in)	BENDING STIFFNESS, EI (lb-in ²) x 10 ⁶	BENDING MOMENT, M (ft-lbf)	SHEAR, V (lbf)	SHEAR DEFL. COEFFICIENT, K (lbf)
PJI-40	9 ¹ / ₂	193	2735	1120	4.94
	11 ⁷ / ₈	330	3545	1420	6.18
	14	482	4270	1710	7.28
	16	657	4950	1970	8.32
PJI-60	9 ¹ / ₂	231	3780	1120	4.94
	11 ⁷ / ₈	396	4900	1420	6.18
	14	584	5895	1710	7.28
	16	799	6835	1970	8.32
PJI-80	11 ⁷ / ₈	547	6940	1420	6.18
	14	802	8360	1710	7.28
	16	1092	9690	1970	8.32
	18	1413	11000	2450	9.36
	20	1790	12180	2530	10.40
	22	2214	13340	2615	11.44
	24	2687	14490	2695	12.48
PJI-90	11 ⁷ / ₈	601	8515	1420	6.18
	14	877	10255	1710	7.28
	16	1187	11895	1970	8.32
	18	1546	13455	2450	9.36
	20	1957	14885	2530	10.40
	22	2419	16305	2615	11.44
	24	2934	17710	2695	12.48

For SI: 1 inch = 25.4 mm; 1 lbf = 4.45 N; 1 lbf-ft = 1.356 N-m; 1 lbf-in² = 0.00287 N-m².

¹Values are reference design values for normal duration of loads. All values except EI and K may be adjusted for other load durations as permitted by the applicable code for solid-sawn lumber.

²Reference design moment capacity (M_r) of I-joists must not be increased by any repetitive member use factor.

³For calculating uniform load and center-point load deflections of the Power Joist[®] in a simple-span application:

$$\text{For uniform loads: } \Delta = \frac{5w\ell^4}{384EI} + \frac{w\ell^2}{K}$$

$$\text{For center-point load: } \Delta = \frac{P\ell^3}{48EI} + \frac{2P\ell}{K}$$

Where:

- Δ = Deflection (inch)
- w = Uniform load (lbf/inch)
- ℓ = Span length (inch)
- P = Concentrated load (lbf)
- EI = Bending stiffness on the I-joist (lbf-in²)
- K = Coefficient of shear deflection (lbf)

TABLE 1B—REFERENCE DESIGN REACTIONS AND FLANGE BEARING CAPACITIES^{1,2,3}

JOIST SERIES	DEPTH (in)	END REACTION (lbf)				INTERIOR REACTION (lbf)				FLANGE BEARING CAPACITY (per in. of brg. length) (lbf/in)
		1.75" Bearing		4" Bearing		3.5" Bearing		5.5" Bearing		
		Web Stiffeners		Web Stiffeners		Web Stiffeners		Web Stiffeners		
		No	Yes	No	Yes	No	Yes	No	Yes	
PJI-40	9 ¹ / ₂	1080	1120	1120	1120	2755	2900	3245	3245	955
	11 ⁷ / ₈	1200	1310	1420	1420	2755	3045	3245	3375	
	14	1200	1480	1550	1710	2755	3175	3245	3485	
	16	1200	1640	1550	1970	2755	3300	3245	3595	
PJI-60	9 ¹ / ₂	1080	1120	1120	1120	2755	2900	3245	3245	1180
	11 ⁷ / ₈	1200	1310	1420	1420	2755	3045	3245	3375	
	14	1200	1480	1550	1710	2755	3175	3245	3485	
	16	1200	1640	1550	1970	2755	3300	3245	3595	
PJI-80	11 ⁷ / ₈	1280	1420	1420	1420	2760	3300	3255	3585	1705
	14	1280	1710	1550	1710	3020	3455	3435	3745	
	16	1280	1845	1550	1970	3265	3600	3600	3900	
	18	N/A	2050	N/A	2450	3200	3950	3650	4350	
	20	N/A	2050	N/A	2530	3200	3950	3650	4350	
	22	N/A	2050	N/A	2615	3200	3950	3650	4350	
	24	N/A	2050	N/A	2695	3200	3950	3650	4350	
PJI-90	11 ⁷ / ₈	1280	1420	1420	1420	2760	3300	3255	3585	2000
	14	1280	1710	1550	1710	3020	3455	3435	3745	
	16	1280	1845	1550	1970	3265	3600	3600	3900	
	18	N/A	2050	N/A	2450	3200	3950	3650	4350	
	20	N/A	2050	N/A	2530	3200	3950	3650	4350	
	22	N/A	2050	N/A	2615	3200	3950	3650	4350	
	24	N/A	2050	N/A	2695	3200	3950	3650	4350	

For **SI**: 1 inch = 25.4 mm; 1 lbf = 4.45 N; 1 lbf/in = 0.175 N/mm.

¹The tabulated reference design reaction values are for normal duration of load and are permitted to be adjusted for other load durations in accordance with the applicable code, provided the flange bearing capacity is not exceeded. Values limited by flange bearing capacity may not be further increased for duration of load. The flange bearing capacity, per inch of bearing length, is based on reference design compression perpendicular-to-grain of the I-joist flange, accounting for eased edges, and may be further limited by the bearing strength of the support material.

²Linear interpolation of the reaction capacity between the minimum and maximum bearing length is permitted. Bearing lengths longer than the maximum do not further increase reaction capacity.

³See Figure 3 for required web stiffener details.

TABLE 2—ALLOWABLE SPAN LENGTHS (ft-in)

JOIST DEPTH (inches)	JOIST DESIGN	ON-CENTER SPACING (inches)			
		12	16	19.2	24
SIMPLE SPANS					
9 ¹ / ₂	PJI-40	18'-0"	16'-5"	15'-6"	14'-6"
	PJI-60	18'-11"	17'-4"	16'-4"	15'-3"
11 ⁷ / ₈	PJI-40	21'-5"	19'-7"	18'-6"	16'-8"
	PJI-60	22'-7"	20'-8"	19'-6"	18'-2"
	PJI-80	24'-11"	22'-8"	21'-4"	19'-10"
	PJI-90	25'-7"	23'-3"	21'-11"	20'-5"
14	PJI-40	24'-4"	22'-3"	20'-6"	18'-4"
	PJI-60	25'-9"	23'-6"	22'-2"	20'-8"
	PJI-80	28'-3"	25'-9"	24'-3"	22'-7"
	PJI-90	29'-0"	26'-5"	24'-11"	23'-2"
16	PJI-40	26'-11"	24'-3"	22'-1"	19'-9"
	PJI-60	28'-6"	26'-0"	24'-7"	22'-10"
	PJI-80	31'-4"	28'-6"	26'-10"	25'-0"
	PJI-90	32'-1"	29'-3"	27'-6"	25'-5"
18	PJI-80	34'-2"	31'-1"	29'-3"	27'-3"
	PJI-90	35'-1"	31'-11"	30'-1"	27'-11"
20	PJI-80	36'-11"	33'-8"	31'-8"	29'-6"
	PJI-90	37'-11"	34'-6"	32'-6"	30'-3"
22	PJI-80	39'-8"	36'-1"	34'-0"	31'-8"
	PJI-90	40'-9"	37'-1"	34'-11"	32'-6"
24	PJI-80	42'-4"	38'-6"	36'-4"	33'-9"
	PJI-90	43'-5"	39'-6"	37'-3"	34'-8"
MULTIPLE SPANS					
9 ¹ / ₂	PJI-40	19'-7"	17'-11"	16'-4"	14'-7"
	PJI-60	20'-8"	18'-10"	17'-9"	16'-6"
11 ⁷ / ₈	PJI-40	23'-5"	20'-5"	18'-7"	16'-7"
	PJI-60	24'-8"	22'-6"	21'-2"	19'-7"
	PJI-80	27'-1"	24'-8"	23'-3"	21'-7"
	PJI-90	27'-11"	25'-4"	23'-10"	21'-10"
14	PJI-40	25'-11"	22'-5"	20'-5"	18'-3"
	PJI-60	28'-0"	25'-7"	24'-1"	19'-9"
	PJI-80	30'-10"	28'-0"	26'-5"	23'-11"
	PJI-90	31'-8"	28'-9"	27'-1"	23'-11"
16	PJI-40	27'-11"	24'-2"	22'-0"	19'-8"
	PJI-60	31'-1"	28'-4"	24'-9"	19'-9"
	PJI-80	34'-2"	31'-1"	29'-3"	23'-11"
	PJI-90	35'-0"	31'-10"	29'-11"	25'-11"
18	PJI-80	37'-3"	33'-10"	31'-11"	29'-5"
	PJI-90	38'-3"	34'-9"	32'-9"	30'-5"
20	PJI-80	40'-3"	36'-8"	34'-6"	31'-0"
	PJI-90	41'-5"	37'-8"	35'-5"	31'-5"
22	PJI-80	43'-3"	39'-4"	36'-4"	31'-5"
	PJI-90	44'-5"	40'-5"	38'-0"	31'-5"
24	PJI-80	46'-2"	41'-6"	37'-10"	31'-5"
	PJI-90	47'-5"	43'-1"	39'-3"	31'-5"

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 psf = 47.88 Pa.

¹Allowable clear span applicable to simple-span or multiple-span residential floor construction with a design dead load of 10 psf and a live load of 40 psf. The live load deflection is limited to L/480 (L = span length in inches). This span chart is based on uniform loads. For applications other than uniformly distributed loads, an engineering analysis may be required based on the use of the design properties in Tables 1A and 1B.

²Spans are based on a composite floor with glue-nailed sheathing meeting the requirements for APA Rated Sheathing STURD-I-FLOOR, conforming to PS 2, with a minimum thickness of ¹⁹/₃₂ inch (40/20 or 20 o.c.) for a joist spacing of 19.2 inches or less, or ²³/₃₂ inch (48/24 or 24 o.c.) for a joist spacing of 24 inches. Adhesive must meet APA Specification AFG-01 or ASTM D3498. Spans must be reduced by 12 inches when floor sheathing is nailed only.

³Minimum bearing length must be 1³/₄ inches for the end bearings and 3¹/₂ inches for the intermediate bearings.

⁴Bearing stiffeners are not required when I-joists are used with the spans and spacings given in the above table, except on 18-, 20-, 22- and 24-inch PJI-80 and PJI-90 joists, and as required for use with hangers.

TABLE 3—LOCATION OF CIRCULAR HOLES IN PJI JOIST WEBS, SIMPLE OR MULTIPLE SPAN FOR DEAD LOADS UP TO 10 psf AND LIVE LOADS UP TO 40 psf^{1,2,3,4,5}

JOIST DEPTH (in)	JOIST SERIES	SAF ⁶	MINIMUM DISTANCE FROM INSIDE FACE OF ANY SUPPORT TO CENTER OF HOLE (ft-in)														
			Round Hole Diameter (in)														
			2	3	4	5	6	6 ¹ / ₄	7	8	8 ⁵ / ₈	9	10	10 ³ / ₄	11	12	12 ³ / ₄
9 ¹ / ₂ "	PJI -40	14'-6"	0'-7"	1'-8"	3'-0"	4'-4"	5'-9"	6'-3"									
	PJI -60	15'-3"	1'-8"	3'-0"	4'-4"	5'-8"	7'-3"	7'-8"									
11 ⁷ / ₈ "	PJI -40	16'-7"	0'-7"	0'-8"	1'-2"	2'-5"	3'-9"	4'-1"	5'-1"	6'-8"	7'-11"						
	PJI -60	18'-2"	0'-8"	1'-10"	3'-2"	4'-5"	5'-10"	6'-2"	7'-4"	8'-11"	10'-0"						
	PJI -80	19'-10"	1'-11"	3'-2"	4'-6"	5'-10"	7'-3"	7'-8"	8'-10"	10'-6"	11'-7"						
	PJI -90	20'-5"	2'-1"	3'-4"	4'-8"	6'-0"	7'-6"	7'-10"	9'-0"	10'-8"	11'-11"						
14"	PJI -40	18'-3"	0'-7"	0'-8"	0'-8"	0'-9"	1'-10"	2'-2"	3'-2"	4'-7"	5'-5"	6'-0"	7'-7"	9'-4"			
	PJI -60	19'-9"	0'-7"	0'-8"	0'-8"	1'-7"	3'-2"	3'-6"	4'-9"	6'-6"	7'-8"	8'-4"	10'-4"	11'-11"			
	PJI -80	22'-7"	0'-7"	1'-9"	3'-0"	4'-4"	5'-8"	6'-1"	7'-1"	8'-7"	9'-7"	10'-3"	12'-2"	13'-10"			
	PJI -90	23'-2"	0'-7"	1'-9"	3'-0"	4'-4"	5'-8"	6'-1"	7'-1"	8'-8"	9'-10"	10'-7"	12'-8"	14'-4"			
16"	PJI -40	19'-8"	0'-7"	0'-8"	0'-8"	0'-9"	0'-9"	0'-10"	1'-5"	2'-9"	3'-7"	4'-1"	5'-6"	6'-7"	7'-0"	8'-9"	10'-9"
	PJI -60	19'-9"	0'-7"	0'-8"	0'-8"	0'-9"	0'-9"	0'-10"	1'-10"	3'-6"	4'-6"	5'-2"	7'-3"	8'-11"	9'-6"	11'-10"	13'-9"
	PJI -80	23'-11"	0'-7"	0'-8"	0'-8"	1'-7"	3'-2"	3'-7"	4'-10"	6'-6"	7'-7"	8'-3"	10'-2"	11'-8"	12'-2"	14'-3"	16'-0"
	PJI -90	25'-5"	0'-7"	0'-8"	1'-8"	2'-11"	4'-3"	4'-7"	5'-7"	7'-0"	8'-1"	8'-9"	10'-8"	12'-2"	12'-8"	14'-10"	16'-7"
18"	PJI -80	27'-3"	0'-7"	0'-8"	0'-8"	0'-11"	2'-3"	2'-8"	3'-9"	5'-2"	6'-1"	6'-8"	8'-3"	9'-6"	9'-11"	11'-8"	13'-0"
	PJI -90	27'-11"	0'-7"	0'-8"	0'-8"	1'-6"	2'-11"	3'-4"	4'-5"	5'-10"	6'-10"	7'-5"	9'-0"	10'-3"	10'-8"	12'-5"	13'-9"
20"	PJI -80	29'-6"	0'-7"	0'-8"	0'-8"	0'-9"	1'-9"	2'-1"	3'-1"	4'-5"	5'-3"	5'-10"	7'-3"	8'-4"	8'-8"	10'-3"	11'-5"
	PJI -90	30'-3"	0'-7"	0'-8"	0'-8"	0'-10"	2'-2"	2'-6"	3'-6"	4'-10"	5'-8"	6'-2"	7'-8"	8'-9"	9'-1"	10'-8"	11'-11"
22"	PJI -80	31'-5"	0'-7"	0'-8"	0'-8"	0'-9"	0'-9"	1'-1"	2'-0"	3'-3"	4'-0"	4'-6"	5'-9"	6'-9"	7'-1"	8'-6"	9'-9"
	PJI -90	31'-5"	0'-7"	0'-8"	0'-8"	0'-9"	0'-10"	1'-1"	2'-0"	3'-3"	4'-2"	4'-9"	6'-4"	7'-7"	8'-0"	9'-8"	11'-0"
24"	PJI -80	31'-5"	0'-7"	0'-8"	0'-8"	0'-9"	0'-9"	0'-10"	0'-10"	1'-11"	2'-7"	3'-1"	4'-4"	5'-5"	5'-10"	7'-4"	8'-6"
	PJI -90	31'-5"	0'-7"	0'-8"	0'-8"	0'-9"	0'-9"	0'-10"	0'-10"	2'-4"	3'-2"	3'-9"	5'-3"	6'-4"	6'-9"	8'-4"	9'-6"

For **S**: 1 inch = 25.4 mm, 1 foot = 304.8 mm.

¹Above tables may be used for I-joist spacing of 24 inches on center or less.

²Hole location distance is measured from inside face of supports to center of hole.

³Distances in this chart are based on a uniformly distributed design dead load of 10 psf (479 Pa), plus a uniformly distributed design live load of 40 psf (1915 Pa).

⁴For continuous joists with more than one span, use the longest span to determine hole location in either span.

⁵Joists with web hole sizes and/or locations that fall outside of the scope of this table must be analyzed based on the actual hole size, joist spacing, span, and loading conditions. The I-joist shear capacity at the location of a circular web hole is calculated using the following equation:

$$V_m = \text{Published Shear Value} \times [(Joist\ Depth - Hole\ Diameter) / Joist\ Depth].$$

⁶SAF = Span Adjustment Factor, used as defined below.

OPTIONAL:

Table 3 is based on the I-joists being used at their maximum span. If the I-joists are placed at less than their full allowable span, the maximum distance from the centerline of the hole to the face of any support (*D*) as given above may be reduced as follows:

$$D_{reduced} = \frac{L_{actual}}{SAF} \times D$$

Where:

D_{reduced} = Distance from the inside face of any support to center of hole, reduced for less-than-maximum span applications (ft). The reduced distance must not be less than 6 inches from the face of the support to edge of the hole.

L_{actual} = The actual measured span distance between the inside faces of supports (ft).

SAF = Span Adjustment Factor given in Table 3.

D = The minimum distance from the inside face of any support to center of hole from Table 3 above.

If $\frac{L_{actual}}{SAF}$ is greater than 1, use 1 in the above calculation for $\frac{L_{actual}}{SAF}$.

Rules for cutting holes in PJI joists:

1. The distance between the inside edge of the support and the centerline of any hole must be in compliance with the requirements of Table 3.
2. I-joist top and bottom flanges must NEVER be cut, notched, or otherwise modified.
3. Whenever possible, field-cut holes should be centered on the middle of the web.
4. The maximum size hole that can be cut into an I-joist web must equal the clear distance between the flanges of the I-joist minus $\frac{1}{4}$ inch. A minimum of $\frac{1}{8}$ inch should always be maintained between the top or bottom of the hole and the adjacent I-joist flange.
5. The sides of square holes or longest sides of rectangular holes must not exceed three fourths of the diameter of the maximum round hole permitted at that location.
6. Where more than one hole is necessary, the distance between adjacent hole edges must exceed twice the diameter of the largest round hole or twice the size of the largest square hole (or twice the length of the longest side of the longest rectangular hole) and each hole must be sized and located in compliance with the requirements of Table 3.
7. $\frac{1}{2}$ -inch holes are permitted anywhere in a cantilevered section of an PJI Joist. Holes of greater size may be permitted subject to verification.
8. A $\frac{1}{2}$ -inch hole can be placed anywhere in the web provided that it meets the requirements of 6 above.
9. For joists with more than one span, use the longest span to determine hole location in either span.
10. All holes must be cut in a workmanlike manner in accordance with the restrictions listed above and as illustrated in Figure 2.
11. Limit three maximum size holes per span.
12. A group of round holes at approximately the same location is permitted if they meet the requirements for a single round hole circumscribed around them.





FIGURE 2—TYPICAL HOLES IN THE WEB



Stiffener Size and Nailing Requirement		
Joist Depth	2-1/2" Wide Flange 8d (2-1/2") nails	3-1/2" Wide Flange 10d (3") nails
9 1/2"	4	-
11 7/8"	4	4
14"	4	4
16"	4	4
18"	-	6
20"	-	6
22"	-	8
24"	-	8
Minimum Stiffener Size	1" x 2-5/16" (width)	1-1/2" x 2-5/16" (width)

Requirements for Web Stiffeners:

1. Wood structural panel web stiffeners must be placed on each side of the I-joist web at:
 - (a) Hangers with side nailing.
 - (b) Hangers which do not laterally support the top flange of the I-joist.
 - (c) Locations where concentrated loads in excess of 1,580 pounds are applied to the top flange of the I-joist between supports or, in the case of cantilever, anywhere between the cantilever tip and the support.
 - (d) At exterior supports in engineered applications where concentrated loads cause exterior reaction loads to exceed 1,580 pounds.
 - (e) At reactions exceeding the tabulated values corresponding to installations without web stiffeners, as shown in Table 1B.
 - (f) At all end reactions on 18-, 20-, 22- and 24-inch PJI-80 and PJI-90 joists.
2. Web stiffeners must be made of Utility grade SPF (south) or better for lumber and/or sheathing grade or better for wood structural panels. When wood structural panels are used as web stiffeners, the strong axis of the panel must be oriented vertically (perpendicular to the long axis of the I-joist).

FIGURE 3—WEB STIFFENER REQUIREMENTS

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. ICC-ES Evaluation Report is a trademark of ICC Evaluation Service, LLC (ICC-ES). The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither ICC-ES, nor APA or its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. The joint ICC-ES/APA Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. Consult the local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because neither APA, nor ICC-ES, has any control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.