



Most Widely Accepted and Trusted

ICC-ES Report

ICC-ES | (800) 423-6587 | (562) 699-0543 | www.icc-es.org

ESR-1636

Reissued 04/2017

This report is subject to renewal 04/2018.

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES

SECTION: 06 11 00—WOOD FRAMING

REPORT HOLDER:

BAMBOO TECHNOLOGIES LLC

**POST OFFICE BOX 1606
13-382 POHOIKI ROAD
PAHOA, HAWAII 96778**

EVALUATION SUBJECT:

STRUCTURAL BAMBOO POLES



Look for the trusted marks of Conformity!

“2014 Recipient of Prestigious Western States Seismic Policy Council (WSSPC) Award in Excellence”



A Subsidiary of  INTERNATIONAL CODE COUNCIL™

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.



ICC-ES Evaluation Report

ESR-1636

Reissued April 2017

This report is subject to renewal April 2018.

www.icc-es.org | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES

Section: 06 11 00—Wood Framing

REPORT HOLDER:

BAMBOO TECHNOLOGIES LLC
POST OFFICE BOX 1606
13-382 POHOIKI ROAD
PAHOA, HAWAII 96778
(808) 572-1007
www.bambooliving.com
bamboo@bambootechnologies.com

EVALUATION SUBJECT:

STRUCTURAL BAMBOO POLES

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2012, 2009 and 2006 *International Building Code*® (IBC)
- 2012, 2009 and 2006 *International Residential Code*® (IRC)
- 1997 *Uniform Building Code*™ (UBC)

Property evaluated:

Structural

2.0 USES

The structural bamboo poles are used as structural elements in wall, roof and floor trusses (panels) or as individual compression and/or tension members, in Type V non-fire-resistance rated residential and commercial construction.

3.0 DESCRIPTION

The structural bamboo poles covered in this report are from Quang Ngai, Vietnam, and are of the Tre Gai (*bambusa stenostachya*) species. The bamboo poles are typically 2¹¹/₁₆ inches (69 mm) to 3¹⁵/₁₆ inches (100 mm) in diameter and 10 feet (3048 mm) to 14 feet (4267 mm) in length, depending on the building type. The structural bamboo poles have a nominal density of 42 pcf (673 kg/m³) and a tolerance of ±15 percent and are preservatives treated with a borate solution.

4.0 DESIGN AND INSTALLATION

4.1 General:

Design and construction practices must take the following into account:

- A design must be provided for lateral bracing to resist wind and seismic forces.
- The structural performance must be assessed by calculating the action effects using a linear material model (elastic behavior).
- The effect of shrinkage must be taken into account in the design of individual structural members, and in the design of the structure as a whole.
- The effects of long-term loading (creep) need to be considered in the design of individual structural members, and in the design of the structure as a whole. Long-term flexural creep in bamboo in bending may be assumed to be 3 to 4 percent of the immediate elastic deformation.

4.2 Design Considerations:

4.2.1 Allowable Design Stresses: Design stresses must not exceed the values noted in Table 1. No adjustment for duration of load can be made, except for permanent load and wind load conditions, as addressed in this section.

For a permanent load condition (more than 10 years), all stresses, except for MOE, must be reduced by 25 percent. For a wind loading condition, the allowable design stresses, except for MOE, are permitted to be increased by 20 percent.

4.2.2 Bamboo Poles (Elements): The design of individual elements must consider the following:

- a. The element retains its elastic behavior, until failure (plastic behavior is considered to be not significant).
- b. The elements are analyzed as variable-thickness, hollow-tube structures.
- c. The elements are analyzed as not perfectly straight members.
- d. The elements are analyzed as tapered members.
- e. Design is conducted in accordance with the following:
 1. Conventional structural analysis methods are used, with definitions of the initial curvature, the diameter and the wall thickness.
 2. Any bamboo joint or support must be considered to act as a hinge, unless substantiating data are submitted to justify consideration as a semi-rigid or a rigid joint.
 3. Bernoulli's theorem (flat cross sections remain flat) is valid for bamboo.
- f. Design of bamboo poles acting as beams must be based on the following items, provided the load is

symmetrical (for asymmetrical loads, applied stresses at critical points must be calculated):

1. The moment of inertia, I , must be determined as follows: The outside diameter and the wall thickness must be measured at both ends. With these values, the mean diameter and the mean wall thickness for the middle of the beam must be calculated. The moment of inertia, I , must be calculated using the mean values. If actual measurements are not available, a conservative approach is permitted assuming the wall thickness to be $\frac{1}{2}$ inch (12 mm) and the outside diameter to be $2\frac{3}{4}$ inches (70 mm).
 2. The initial curvature must be considered in the calculation of the deflection.
 3. If the length of the beam is less than 25 times the diameter at the small end, the shear stress in the neutral layer at that end must be checked.
 4. Forces acting on a beam (loads or reaction forces at supports) must act at nodes or as near to nodes as possible, not exceeding 4 inches from the nodes.
 5. For beams in which combined axial and bending loads occur, the interaction of applied stresses must be considered.
- g. Design of bamboo poles acting as columns must be based on one of the following:
1. Results of compression buckling tests on full-size specimens.
 2. Calculations based on the following:
 - (a) The moment of inertia (I) must be determined in accordance with Section 6.6.1 of the INBAR document in Appendix A of the ICC-ES Acceptance Criteria for Structural Bamboo (AC162).
 - (b) The bending stresses due to initial curvature, eccentricities and induced deflection must be taken into account.
 - (c) Buckling calculation must be in accordance with the Euler equation, using a reduction to 90 percent of the moment of inertia. [The reduction to 90 percent takes into account the effect of the taper, provided the taper (defined as the ratio of the difference between the minimum and maximum outer diameters to the length) is less than 1:170.]

4.2.3 Connections: Connections must be designed to achieve structural continuity between elements. Connection

designs shall be based on complete full-size tests of the connector for a given load and geometry. This includes fastening elements.

5.0 CONDITIONS OF USE

The structural bamboo poles described in this report comply as an alternative material and method of construction as noted in those codes specifically listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 Design and analysis must comply with the details noted in this report.
- 5.2 Calculations, drawings and required reports of connection and compression tests, as noted in Sections 4.2 in this report, must be furnished to the building official, verifying that the material is used in accordance with this report. The drawings and calculations must be prepared by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.
- 5.3 Special inspection may be required by the code official for the assembly of the finished product at the jobsite, in accordance with Section 1704.13 (2006), 1704.15 (2009) or 1705.1.1 (2012) of the IBC or Section 1701.5 (item 15) of the UBC, whichever is applicable.
- 5.4 The bamboo must be limited to end-use locations at which the average equilibrium moisture content of the material is equal to or less than 16 percent.
- 5.5 The bamboo must be processed at Bamboo Hardwoods Vietnam, Thoi Hoa Village, Ben Cat District, Binh Duong Province, Vietnam, with inspections by ICC-ES and SGS Vietnam (AA-701).

6.0 EVIDENCE SUBMITTED

- 6.1 Descriptive details
- 6.2 A quality control manual
- 6.3 An analysis and results of tests verifying compliance with the ICC-ES Acceptance Criteria for Structural Bamboo (AC162), dated March 2000 (editorially revised October 2013).

7.0 IDENTIFICATION

The structural bamboo poles must be identified with a stamp indicating “Certified Pole,” the name of the inspection agency (SGS Vietnam), the evaluation report number (ESR-1636), and the words “Borate Treated.”

TABLE 1—ALLOWABLE DESIGN STRESSES

PRODUCT	BENDING STRENGTH, F_b (psi)	MODULUS OF ELASTICITY, MOE (psi)	COMPRESSIVE STRENGTH, F_c (psi)	HORIZONTAL (LONGITUDINAL) SHEAR STRENGTH, F_v (psi)	TENSILE STRENGTH, F_t (psi)
Structural bamboo pole	1,500	1.7×10^6	590	185	1,110

¹Allowable design stresses are based on values derived from testing in accordance with AC162. Factors have been applied as noted in Sections 3.3.2 and 3.3.3 of AC162. No adjustment for duration of load shall be made, except for a permanent load condition, and as noted in Section 4.2.1 of this report. For a permanent load condition (more than 10 years), all stresses, except for MOE, must be reduced by 25 percent.

²Allowable values are based on covered dry conditions of use, defined as those environmental conditions represented by sawn lumber with an equilibrium moisture content of less than 16 percent.

³Tensile strength noted is the result of small-scale tension tests. See Section 4.2.2 in this report for additional information.