

ICC-ES Evaluation Report

ESR-3037

Reissued August 2024

This report also contains:



- LABC Supplement

Subject to renewal August 2025

- FBC Supplement

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2024 ICC Evaluation Service, LLC. All rights reserved.

<p>DIVISION: 03 00 00— CONCRETE</p> <p>Section: 03 16 00— Concrete Anchors</p> <p>DIVISION: 05 00 00— METALS</p> <p>Section: 05 05 19—Post- installed Concrete Anchors</p>	<p>REPORT HOLDER:</p> <p>SIMPSON STRONG-TIE COMPANY INC.</p> 	<p>EVALUATION SUBJECT:</p> <p>SIMPSON STRONG-TIE® STRONG-BOLT® 2 WEDGE ANCHOR FOR CRACKED AND UNCRACKED CONCRETE</p>	
--	--	--	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2021, 2018, 2015, 2012, and 2009 [International Building Code® \(IBC\)](#)
- 2021, 2018, 2015, 2012, and 2009 [International Residential Code® \(IRC\)](#)

For evaluation for compliance with codes adopted by the [Los Angeles Department of Building and Safety \(LADBS\)](#), see [ESR-3037 LABC and LARC Supplement](#).

Property evaluated:

- Structural

2.0 USES

The ¹/₄-inch (6.4 mm) Simpson Strong-Tie® Strong-Bolt® 2 wedge anchor is used as anchorage to resist static, wind and seismic tension and shear loads in uncracked normal-weight concrete and lightweight concrete having a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa). The ³/₈-inch-through 1-inch-diameter (9.5 mm through 25.4 mm) anchors are used as anchorage to resist static, wind and seismic tension and shear loads in cracked and uncracked normal-weight concrete and lightweight concrete having a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa).

The ³/₈-inch-, ¹/₂-inch-, ⁵/₈-inch- and ³/₄-inch-diameter (9.5 mm, 12.7 mm, 15.9 mm and 19.1 mm) anchors may be installed in the soffit of cracked and uncracked normal-weight or sand-lightweight concrete-filled steel deck having a minimum specified compressive strength, f'_c , of 3,000 psi (20.7 MPa), as shown in [Figures 5 and 6](#).

The ³/₈-inch- and ¹/₂-inch-diameter (9.5 mm and 12.7 mm) anchors may be installed in the topside of cracked and uncracked normal-weight or sand-lightweight concrete-filled steel deck having a minimum member thickness, $h_{min,deck}$, as noted in [Table 5](#) of this report and a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa), as shown in [Figure 7](#).

The Strong-Bolt® 2 complies with Section [1901.3](#) of the 2021, 2018 and 2015 IBC, Section [1909](#) of the 2012 IBC, and Section [1912](#) of the 2009 IBC. The anchors are alternatives to cast-in-place anchors described in Section [1908](#) of the 2012 IBC, and Section [1911](#) of the 2009 IBC. The anchors may also be used where an engineered design is submitted in accordance with Section [R301.1.3](#) of the IRC.

3.0 DESCRIPTION

3.1 Strong-Bolt[®] 2:

3.1.1 General: Strong-Bolt[®] 2 anchors are torque-controlled, mechanical expansion anchors consisting of an anchor body, expansion clip, nut, and washer. A typical anchor (carbon steel version) is shown in [Figure 1](#) of this report. The anchor body has a tapered mandrel formed on the installed end of the anchor and a threaded section at the opposite end. The taper of the mandrel increases in diameter toward the installed end of the anchor. The three-segment expansion clip wraps around the tapered mandrel. Before installation, this expansion clip is free to rotate about the mandrel. The anchor is installed in a predrilled hole. When the anchor is set by applying torque to the hex nut, the mandrel is drawn into the expansion clip, which engages the drilled hole and transfers the load to the base material. Pertinent dimensions are as set forth in [Tables 1A](#) and [1B](#) of this report.

3.1.2 Strong-Bolt[®] 2, Carbon Steel: The anchor bodies are manufactured from carbon steel material with zinc plating conforming to [ASTM B633](#), SC1, Type III. The expansion clip for the 1/4-inch-, 3/8-inch-, 1/2-inch-, 5/8-inch- and 3/4-inch-diameter carbon steel Strong-Bolt 2 anchors is fabricated from carbon steel and conforms to [ASTM A568](#). The expansion clip for the 1-inch-diameter carbon steel Strong-Bolt 2 anchor is fabricated from stainless steel and conforms to [ASTM A240](#), Grade 316. The hex nut for the carbon steel Strong-Bolt 2 anchor conforms to [ASTM A563](#), Grade A. The washer for the carbon steel Strong-Bolt 2 anchor conforms to [ASTM F844](#). The available anchor diameters under this report are 1/4 inch, 3/8 inch, 1/2 inch, 5/8 inch, 3/4 inch and 1 inch (6.4 mm, 9.5 mm, 12.7 mm, 15.9 mm, 19.1 mm, and 25.4 mm).

3.1.3 Strong-Bolt[®] 2, Stainless Steel: The anchor bodies of the stainless steel Strong-Bolt 2 anchors are manufactured from either AISI Type 304 or AISI Type 316 stainless steel. The expansion clip for the stainless steel Strong-Bolt 2 anchor conforms to AISI Type 304 or AISI Type 316 stainless steel. The hex nut and washer for the Type 304 and Type 316 stainless steel Strong-Bolt 2 conform to AISI Type 304 and Type 316 steel, respectively. The available anchor diameters under this report are 1/4 inch, 3/8 inch, 1/2 inch, 5/8 inch and 3/4 inch (6.4 mm, 9.5 mm, 12.7 mm, 15.9 mm and 19.1 mm).

3.2 Concrete:

Normal-weight and lightweight concrete must conform to Sections [1903](#) and [1905](#) of the IBC, as applicable.

3.3 Profile Steel Deck:

The profile steel deck must comply with the configuration in [Figures 5, 6](#) and [7](#) and have a minimum base-steel thickness of 0.035 inch (0.889 mm) [20 gauge]. Steel must comply with [ASTM A653/A653M](#) SS Grade 33 with a minimum yield strength of 33,000 psi (228 MPa) for [Figures 5](#) and [7](#), and Grade 50 with a minimum yield strength of 50,000 psi (345 MPa) for [Figure 6](#).

4.0 DESIGN AND INSTALLATION

4.1 Strength Design:

4.1.1 General: Design strength of anchors complying with the 2021 IBC as well as Section R301.1.3 of the 2021 IRC, must be determined in accordance with [ACI 318-19](#) Section 17 and this report.

Design strength of anchors complying with the 2018 and 2015 IBC as well as Section R301.1.3 of the 2018 and 2015 IRC, must be determined in accordance with [ACI 318-14](#) Section 17 and this report.

Design strength of anchors complying with the 2012 IBC, as well as Section [R301.1.3](#) of the 2012 IRC, must be determined in accordance with [ACI 318-11](#) Appendix D and this report.

Design strength of anchors complying with the 2009 IBC and Section [R301.1.3](#) of the 2009 IRC must be in accordance with [ACI 318-08](#) Appendix D and this report.

Design parameters provided in [Tables 1A](#) through [6](#) and references to [ACI 318](#) are based on the 2021 IBC (ACI 318-19), on the 2018 and 2015 IBC (ACI 318-14) and on the 2012 IBC (ACI 318-11) unless noted otherwise in Sections 4.1.1 through [4.1.12](#) of this report. The strength design of anchors must comply with ACI 318-19 17.5.1.2, ACI 318-14 17.3.1 or ACI 318-11 D.4.1, as applicable, except as required in ACI 318-19 17.10, ACI 318-14 17.2.3 or ACI 318-11 D.3.3, as applicable.

Strength reduction factors, ϕ , as given in ACI 318-19 17.5.3, ACI 318-14 17.3.3 or ACI 318-11 D.4.3, as applicable, must be used for load combinations calculated in accordance with Section [1605.1](#) of the 2021 IBC or Section [1605.2](#) of the 2018, 2015, 2012 and 2009 IBC and Section 5.3 of ACI 318 (-19 and -14) or Section 9.2 of ACI 318-11, as applicable. Strength reduction factors, ϕ , as given in ACI 318-11 D.4.4 must be used for load combinations calculated in accordance with ACI 318-11 Appendix C.

The value of f'_c used in the calculations must be limited to 8,000 psi (55.2 MPa), maximum, in accordance with ACI 318-19 17.3.1, ACI 318-14 17.2.7 or ACI 318-11 D.3.7, as applicable.

4.1.2 Requirements for Static Steel Strength in Tension: The nominal steel strength of a single anchor in tension, N_{sa} , in accordance with ACI 318-19 17.6.1.2, ACI 318-14 17.4.1.2 or ACI 318-11 D.5.1.2, as applicable, is given in [Tables 2A](#) and [2B](#) of this report. The strength reduction factor, ϕ , corresponding to a brittle steel element must be used for the carbon steel 1-inch-diameter anchor as described in [Table 2A](#) of this report. For all other anchors the strength reduction factor, ϕ , corresponding to a ductile steel element must be used as described in [Tables 2A](#) and [2B](#) of this report.

4.1.3 Requirements for Static Concrete Breakout Strength in Tension: The nominal concrete breakout strength of a single anchor or group of anchors in tension, N_{cb} and N_{cbg} , must be calculated in accordance with ACI 318-19 17.6.2, ACI 318-14 17.4.2 or ACI 318-11 D.5.2, as applicable, with modifications as described in this section. The basic concrete breakout strength in tension, N_b , must be calculated in accordance with ACI 318-19 17.6.2.2, ACI 318-14 17.4.2.2 or ACI 318-11 D.5.2.2, as applicable, using the values of h_{ef} and k_{cr} as described in [Tables 2A](#) and [2B](#) of this report. The nominal concrete breakout strength in tension, N_{cb} or N_{cbg} , in regions of a concrete member where analysis indicates no cracking at service loads in accordance with ACI 318-19 17.6.2.5, ACI 318-14 17.4.2.6 or ACI 318-11 D.5.2.6, as applicable, must be calculated with the value of k_{uncr} as given in [Tables 2A](#) and [2B](#) of this report and with $\Psi_{c,N} = 1.0$, as described in [Tables 2A](#) and [2B](#) of this report.

For anchors installed in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, as shown in [Figures 5](#) and [6](#), determination of the concrete breakout strength in accordance with ACI 318-19 17.6.2, ACI 318-14 17.4.2 or ACI 318-11 D.5.2, as applicable, is not required.

4.1.4 Requirements for Static Pullout Strength in Tension: The nominal pullout strength of a single anchor in tension in accordance with ACI 318-19 17.6.3, ACI 318-14 17.4.3 or ACI 318-11 D.5.3, as applicable, in cracked and uncracked concrete, $N_{p,cr}$ and $N_{p,uncr}$, is given in [Tables 2A](#) and [2B](#) of this report. Where analysis indicates no cracking at service load levels in accordance with ACI 318-19 17.6.3.3, ACI 318-14 17.4.3.6 or ACI 318-11 D.5.3.6, as applicable, the nominal pullout strength in uncracked concrete, $N_{p,uncr}$, applies. Where values for $N_{p,cr}$ or $N_{p,uncr}$ are not provided in [Tables 2A](#) and [2B](#), the pullout strength does not need to be considered. In lieu of ACI 318-19 17.6.3.3, ACI 318-14 17.4.3.6 or ACI 318-11 D.5.3.6, as applicable, $\Psi_{c,p} = 1.0$ for all design cases. The nominal pullout strength in cracked concrete must be adjusted for concrete strengths according to Eq-1:

$$N_{p,f_c} = N_{p,cr} \left(\frac{f'_c}{2,500} \right)^n \quad (\text{lb, psi}) \quad (\text{Eq-1})$$

$$N_{p,f_c} = N_{p,cr} \left(\frac{f'_c}{17.2} \right)^n \quad (\text{N, MPa})$$

where f'_c is the specified compressive strength and n is the factor defining the influence of concrete strength on the pullout strength. For the stainless steel $3/8$ -inch-diameter anchor in cracked concrete n is 0.3. For the stainless steel $5/8$ -inch-diameter anchor in cracked concrete n is 0.4. For all other cases n is 0.5.

In regions where analysis indicates no cracking in accordance with ACI 318-19 17.6.3.3, ACI 318-14 17.4.3.6 or ACI 318-11 D.5.3.6, as applicable, the nominal pullout strength in tension must be adjusted by calculation according to Eq-2:

$$N_{p,f_c} = N_{p,uncr} \left(\frac{f'_c}{2,500} \right)^n \quad (\text{lb, psi}) \quad (\text{Eq-2})$$

$$N_{p,f_c} = N_{p,uncr} \left(\frac{f'_c}{17.2} \right)^n \quad (\text{N, MPa})$$

where f'_c is the specified compressive strength and n is the factor defining the influence of concrete strength on the pullout strength. For the stainless steel $3/8$ -inch-diameter anchor in uncracked concrete, n is 0.3. For the stainless steel $1/4$ -inch-diameter anchor and stainless steel $3/4$ -inch-diameter anchor in uncracked concrete, n is 0.4. For all other cases, n is 0.5.

The pullout strength in cracked and uncracked concrete for anchors installed in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, as shown in [Figures 5](#) and [6](#), is given in [Tables 4A](#), [4B](#) and [4C](#) of this report. The nominal pullout strength in cracked concrete must be adjusted for concrete strength according to Eq-1, using the value of $N_{p,deck,cr}$ in lieu of $N_{p,cr}$, and the value of 3,000 psi (20.7 MPa) must be substituted for the value of 2,500 psi (17.2 MPa) in the denominator. Where analysis indicates no cracking at service load levels in accordance with ACI 318-19 17.6.3.3, ACI 318-14 17.4.3.6 or ACI 318-11 D.5.3.6, as applicable, the nominal pull out strength in uncracked concrete must be adjusted for concrete strength according to Eq-2, using the value of $N_{p,deck,uncr}$ in lieu of $N_{p,uncr}$, and the value of 3,000 psi (20.7 MPa) must be substituted for the value of 2,500 psi (17.2 MPa) in the denominator. The value of $\Psi_{c,p} = 1.0$ for all cases.

4.1.5 Requirements for Static Steel Strength in Shear: The nominal steel strength in shear, V_{sa} , of a single anchor in accordance with ACI 318-19 17.7.1.2, ACI 318-14 17.5.1.2 or ACI 318-11 D.6.1.2, as applicable, is given in [Tables 3A](#) and [3B](#) of this report and must be used in lieu of values derived by calculation from ACI 318-19 Eq. 17.7.1.2b, ACI 318-14 Eq. 17.5.1.2b or ACI 318-11, Eq. D-29, as applicable. The strength reduction factor, ϕ , corresponding to a brittle steel element must be used for the carbon steel 1-inch-diameter anchor as described in [Table 3A](#) of this report. For all other anchors the strength reduction factor, ϕ , corresponding to a ductile steel element must be used for all anchors as described in [Tables 3A](#) and [3B](#) of this report.

The shear strength, $V_{sa,deck}$, of anchors installed in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, as shown in [Figures 5](#) and [6](#), is given in [Tables 4A](#), [4B](#) and [4C](#) of this report.

4.1.6 Requirements for Static Concrete Breakout Strength in Shear: The nominal concrete breakout strength of a single anchor or group of anchors in shear, V_{cb} or V_{cbg} , must be calculated in accordance with ACI 318-19 17.7.2, ACI 318-14 17.5.2 or ACI 318-11 D.6.2, as applicable, with modifications as described in this section. The basic concrete breakout strength in shear, V_b , must be calculated in accordance with ACI 318-19 17.7.2.2.1, ACI 318-14 17.5.2.2 or ACI 318-11 D.6.2.2, as applicable, using the values of ℓ_e and d_a provided in [Tables 3A](#) and [3B](#) of this report.

For anchors installed in the topside of concrete-filled steel deck assemblies, as shown in [Figure 7](#), the nominal concrete breakout strength of a single anchor or group of anchors in shear, V_{cb} or V_{cbg} , respectively, must be calculated in accordance with ACI 318-19 17.7.2, ACI 318-14 17.5.2 or ACI 318-11 D.6.2, as applicable, using the actual member thickness, $h_{min,deck}$, in the determination of A_{vc} . Minimum member topping thickness for anchors in the topside of concrete-filled steel deck assemblies is given in [Table 5](#) of this report.

For anchors installed in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, as shown in [Figures 5](#) and [6](#), calculation of the concrete breakout strength in accordance with ACI 318-19 17.7.2, ACI 318-14 17.5.2 or ACI 318-11 D.6.2, as applicable, is not required.

4.1.7 Requirements for Static Concrete Pryout Strength in Shear: The nominal concrete pryout strength of a single anchor or group of anchors in shear, V_{cp} or V_{cpg} , must be calculated in accordance with ACI 318-19 17.7.3, ACI 318-14 17.5.3 or ACI 318-11 D.6.3, as applicable, modified by using the value of k_{cp} described in [Tables 3A](#) and [3B](#) of this report and the value of N_{cb} or N_{cbg} as calculated in accordance with Section [4.1.3](#) of this report.

For anchors installed in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, as shown in [Figures 5](#) and [6](#), calculation of the concrete pryout strength in accordance with ACI 318-19 17.7.3, ACI 318-14 17.5.3 or ACI 318-11 D.6.3, as applicable, is not required.

4.1.8 Requirements for Seismic Design:

4.1.8.1 General: For load combinations including seismic, the design must be performed in accordance with ACI 318-19 17.10, ACI 318-14 17.2.3 or ACI 318-11 D.3.3, as applicable. Modifications to ACI 318-19 17.10 or ACI 318-14 17.2.3 shall be applied under Section [1905.1.8](#) of the 2021, 2018 and 2015 IBC, as applicable. For the 2012 IBC, Section [1905.1.9](#) must be omitted. Modifications to ACI 318-08 D.3.3, must be applied under Section [1908.1.9](#) of the 2009 IBC.

The carbon steel 1-inch-diameter anchor complies with ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable, as a brittle steel element. All other anchors comply with ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable, as ductile steel elements and must be designed in accordance with ACI 318-19 17.10.5, 17.10.6 or 17.10.7 or ACI 318-14 Section 17.2.3.4, 17.2.3.5, or 17.2.3.6 or ACI 318-11 Section D.3.3.4, D.3.3.5, or D.3.3.6 or ACI 318-08 Section D.3.3.4, D.3.3.5 or D.3.3.6, as applicable, with the modifications noted above.

4.1.8.2 Seismic Tension: The nominal steel strength and nominal concrete breakout strength for anchors in tension must be calculated in accordance with ACI 318-19 17.6.1 and 17.6.2, ACI 318-14 17.4.1 and 17.4.2 or ACI 318-11 D.5.1 and D.5.2, as applicable, as described in Sections [4.1.2](#) and [4.1.3](#) of this report.

In accordance with ACI 318-19 17.6.3.2.1, ACI 318-14 17.4.3.2 or ACI 318-11 D.5.3.2, as applicable, the appropriate value for nominal pullout strength in tension for seismic loads, $N_{p,eq}$ or $N_{p,deck,eq}$, provided in [Tables 2A](#), [2B](#), [4A](#), [4B](#) and [4C](#) of this report, must be used in lieu of N_p . If no values for $N_{p,eq}$ or $N_{p,deck,eq}$ are given in [Tables 2A](#), [2B](#), [4A](#), [4B](#) or [4C](#), the pullout strength for seismic loads need not be evaluated. The values of $N_{p,eq}$ or $N_{p,deck,eq}$ can be adjusted for concrete strength according to Section [4.1.4](#).

4.1.8.3 Seismic Shear: The nominal concrete breakout and concrete pryout strength for anchors in shear must be calculated in accordance with ACI 318-19 17.7.2 and 17.7.3, ACI 318-14 17.5.2 and 17.5.3 or ACI 318-11 D.6.2 and D.6.3, as applicable, as described in Sections 4.1.6 and 4.1.7 of this report. In accordance with ACI 318-19 17.7.1.2, ACI 318-14 17.5.1.2 or ACI 318-11 D.6.1.2, as applicable, the appropriate value for nominal steel strength in shear for seismic loads, $V_{sa,eq}$ or $V_{sa,deck,eq}$, provided in [Tables 3A](#), [3B](#), [4A](#), [4B](#) and [4C](#) of this report, must be used in lieu of V_{sa} .

4.1.9 Requirements for Interaction of Tensile and Shear Forces: For loadings that include combined tension and shear, the design must be performed in accordance with ACI 318-19 17.8, ACI 318-14 17.6 or ACI 318-11 D.7, as applicable.

4.1.10 Requirements for Critical Edge Distance: In applications where $c < c_{ac}$ and supplemental reinforcement to control splitting of the concrete is not present, the concrete breakout strength in tension for uncracked concrete, calculated according to ACI 318-19 17.6.2, ACI 318-14 17.4.2 or ACI 318-11 D.5.2, as applicable, must be further multiplied by the factor $\Psi_{cp,N}$ given by Eq-3:

$$\Psi_{cp,N} = \frac{c}{c_{ac}} \quad (\text{Eq-3})$$

where the factor $\Psi_{cp,N}$ need not be taken as less than $\frac{1.5h_{ef}}{c_{ac}}$. For all other cases, $\Psi_{cp,N} = 1.0$. In lieu of ACI 318-19 17.9.5, ACI 318-14 17.7.6 or ACI 318-11 D.8.6, as applicable, values of c_{ac} provided in [Tables 1A](#) and [1B](#) of this report must be used.

4.1.11 Requirements for Minimum Member Thickness, Minimum Anchor Spacing and Minimum Edge Distance: In lieu of ACI 318-14 17.7.1 and 17.7.3 or ACI 318-11 D.8.1 and D.8.3, as applicable, values of s_{min} and c_{min} provided in [Tables 1A](#) and [1B](#) of this report must be used. In lieu of ACI 318-19 17.9.4, ACI 318-14 17.7.5 or ACI 318-11 D.8.5, as applicable, minimum member thickness, h_{min} , must be in accordance with [Tables 1A](#) and [1B](#) of this report.

For $3/4$ -inch-diameter carbon steel, and $3/8$ -inch-, $1/2$ -inch- and $5/8$ -inch-diameter stainless steel Strong-Bolt[®] 2 anchors, additional combinations for minimum edge distance c_{min} and minimum spacing s_{min} may be derived by linear interpolation between the boundary given in [Tables 1A](#) and [1B](#) and as shown in [Figure 4](#) of this report.

For anchors installed in the topside of normal-weight or sand-lightweight concrete over profile steel deck floor and roof assemblies, the anchor must be installed in accordance with [Table 5](#) for carbon steel anchors and stainless steel anchors, and [Figure 7](#) of this report.

For anchors installed in the soffit of steel deck assemblies, the anchors must be installed in accordance with [Figures 5](#) and [6](#), and must have a minimum axial spacing along the flute equal to the greater of $3h_{ef}$ or 1.5 times the flute width.

4.1.12 Lightweight Concrete: For the use of anchors in lightweight concrete the modification factor λ_a equal to 0.8λ is applied to all values of $\sqrt{f'_c}$ affecting N_n and V_n .

For ACI 318-19 (2021 IBC), ACI 318-14 (2018 and 2015 IBC), ACI 318-11 (2012 IBC) and ACI 318-08 (2009 IBC), λ shall be determined in accordance with the corresponding version of ACI 318.

For anchors installed in the soffit of sand-lightweight concrete-filled steel deck and floor and roof assemblies, further reduction of the pullout values provided in this report is not required.

4.2 Allowable Stress Design (ASD):

4.2.1 General: Where design values for use with allowable stress design (working stress design) load combinations calculated in accordance with Section 1605.1 of the 2021 IBC or Section [1605.3](#) of the 2018, 2015, 2012 and 2009 IBC, must be established using the following equations:

$$T_{allowable,ASD} = \frac{\phi N_n}{\alpha} \quad (\text{Eq-3})$$

and

$$V_{allowable,ASD} = \frac{\phi V_n}{\alpha} \quad (\text{Eq-4})$$

where:

$T_{allowable,ASD}$ = Allowable tension load (lbf or kN)

$V_{allowable,ASD}$ = Allowable shear load (lbf or kN)

ϕN_n = Lowest design strength of an anchor or anchor group in tension as determined in accordance with ACI 318 (-19 and -14) Chapter 17 and 2021, 2018 and 2015 IBC Section 1905.1.8, ACI 318-11 Appendix D, ACI 318-08 Appendix D, and 2009 IBC Section 1908.1.9, and Section [4.1](#) of this report, as applicable. (lbf or kN). For the 2012 IBC, Section 1905.1.9 must be omitted.

ϕV_n = Lowest design strength of an anchor or anchor group in shear as determined in accordance with ACI 318 (-19 and -14) Chapter 17 and 2021, 2018 and 2015 IBC Section 1905.1.8, ACI 318-11 Appendix D, ACI 318-08 Appendix D, and 2009 IBC Section 1908.1.9, and Section [4.1](#) of this report, as applicable (lbf or kN). For the 2012 IBC, Section 1905.1.9 must be omitted.

α = A conversion factor calculated as a weighted average of the load factors for the controlling load combination. In addition, α shall include all applicable factors to account for non-ductile failure modes and required over-strength.

The requirements for member thickness, edge distance and spacing, as described in this report, must apply.

4.2.2 Interaction of Tensile and Shear Forces: The interaction of tension and shear loads must be consistent with ACI 318-19 17.8, ACI 318-14 17.6 or ACI 318-11, -08, -05 D.7, as applicable, as follows:

If $T_{applied} \leq 0.2T_{allowable,ASD}$, then the full allowable strength in shear, $V_{allowable,ASD}$, must be permitted.

If $V_{applied} \leq 0.2V_{allowable,ASD}$, then the full allowable strength in tension, $T_{allowable,ASD}$, must be permitted.

For all other cases: $\frac{T_{applied}}{T_{allowable,ASD}} + \frac{V_{applied}}{V_{allowable,ASD}} \leq 1.2$

4.3 Installation:

Installation parameters are provided in [Tables 1A](#) and [1B](#) and [4A](#), [4B](#) and [4C](#), and in [Figures 2](#), [3](#), [5](#), [6](#) and [7](#). Anchor locations must comply with this report and the plans and specifications approved by the code official. The Strong-Bolt[®] 2 must be installed in accordance with the manufacturer's published instructions and this report. Anchors must be installed in holes drilled into the concrete using carbide-tipped drill bits conforming to [ANSI B212.15-1994](#). The nominal drill bit diameter must be equal to the nominal diameter of the anchor. The minimum drilled hole depth, h_{hole} , is given in [Tables 1A](#) and [1B](#). The drilled hole must be cleaned, with all dust and debris removed using compressed air. The anchor, nut, and washer must be assembled so that the top of the nut is flush with the top of the anchor. The anchor must be driven into the hole using a hammer until the proper embedment depth is achieved. The nut and washer must be tightened against the base material or material to be fastened until the appropriate installation torque value specified in [Tables 1A](#) and [1B](#) is achieved.

For anchors installed in the topside of normal-weight or sand-lightweight concrete over profile steel deck floor and roof assemblies, installation parameters are provided in [Table 5](#) and in [Figure 7](#) of this report.

For installation in the soffit of normal-weight or sand-lightweight concrete over profile steel deck floor and roof assemblies, the hole diameter in the steel deck must not exceed the diameter of the hole in the concrete by more than $1/8$ inch (3.2 mm). The minimum drilled hole depth, h_{hole} , is given in [Tables 4A](#), [4B](#) and [4C](#). For edge distance and member thickness requirements for installations into the soffit of concrete over steel deck assemblies, see [Figures 5](#) and [6](#). For installation in the soffit of sand-lightweight or normal-weight concrete over profile steel deck floor and roof assemblies, torque must be applied until the appropriate installation torque value specified in [Tables 4A](#), [4B](#) and [4C](#) is achieved.

4.4 Special Inspection:

Periodic special inspection is required in accordance with Section [1705.1.1](#) and Table [1705.3](#) of the 2021, 2018, 2015, and 2012 IBC or Section [1704.15](#) of the 2009 IBC, as applicable. The special inspector must make periodic inspections during anchor installation to verify anchor type, anchor dimensions, concrete type, concrete compressive strength, drill-bit type, hole dimensions, hole cleaning procedures, anchor spacing, edge distances, concrete member thickness, anchor embedment, tightening torque and adherence to the manufacturer's published installation instructions. The special inspector must be present as often as required by the "statement of special inspection." Under the IBC, additional requirements as set forth in Sections [1705](#), [1706](#) and [1707](#) must be observed, where applicable.

5.0 CONDITIONS OF USE:

The Simpson Strong-Tie[®] Strong Bolt[®] 2 wedge anchor described in this report complies with, or is a suitable alternative to what is specified in, those codes listed in Section [1.0](#) of this report, subject to the following conditions:

- 5.1 The anchors must be installed in accordance with the manufacturer's published installation instructions and this report. In case of a conflict, this report governs.
- 5.2 Anchor sizes, dimensions and minimum embedment depths are as set forth in this report.
- 5.3 The 1/4-inch-diameter (6.4 mm) anchors must be limited to use in uncracked normal-weight concrete and lightweight concrete having a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa).

The anchor may also be installed in the top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Tables 1A](#) & [1B](#).

- 5.4 The $3/8$ -inch- through 1-inch-diameter (9.5 mm through 25.4 mm) anchors must be installed in cracked and uncracked normal-weight and lightweight concrete having a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa).

The anchors may also be installed in the top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Tables 1A & 1B](#).

- 5.5 The $\frac{3}{8}$ -inch through $\frac{3}{4}$ -inch-diameter (9.5 mm through 19.1 mm) carbon steel anchors must be installed in the soffit of cracked and uncracked sand-lightweight or normal-weight concrete over profile steel deck having a minimum specified compressive strength, f'_c , of 3,000 psi (20.7 MPa).
- 5.6 The $\frac{3}{8}$ -inch- and $\frac{1}{2}$ -inch-diameter (9.5 mm and 12.7 mm) anchors may be installed in the topside of cracked and uncracked normal-weight or sand-lightweight concrete-filled steel deck having a minimum specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa).
- 5.7 The value of f'_c used for calculation purposes must not exceed 8,000 psi (55.2 MPa).
- 5.8 The concrete shall have attained its minimum design strength prior to installation of the anchors.
- 5.9 Strength design values must be established in accordance with Section [4.1](#) of this report.
- 5.10 Allowable stress design values are established in accordance with Section [4.2](#) of this report.
- 5.11 Anchor spacing and edge distance, as well as minimum member thickness, must comply with [Tables 1A, 1B, 4A, 4B, 4C, 5](#); and [Figures 4, 5, 6, and 7](#) of this report.
- 5.12 Prior to anchor installation, calculations and details demonstrating compliance with this report must be submitted to the code official. The calculations and details must be prepared by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.
- 5.13 Since an ICC-ES acceptance criteria for evaluating data to determine the performance of expansion anchors subjected to fatigue or shock loading is unavailable at this time, the use of these anchors under such conditions is beyond the scope of this report.
- 5.14 The $\frac{3}{8}$ -inch through 1-inch (9.5 mm through 25.4 mm) anchors may be installed in regions of concrete where cracking has occurred or where analysis indicates cracking may occur ($f_t > f_r$), subject to the conditions of this report.
- 5.15 The $\frac{1}{4}$ -inch-diameter (6.4 mm) anchors may be used to resist short-term loading due to wind or seismic forces, in locations designated as Seismic Design Categories A and B under the IBC, subject to the conditions of this report.
- 5.16 The $\frac{3}{8}$ -inch through 1-inch (9.5 mm through 25.4 mm) anchors may be used to resist short-term loading due to wind or seismic forces, in locations designated as Seismic Design Categories A through F under the IBC, subject to the conditions of this report.
- 5.17 Where not otherwise prohibited in the code, Strong-Bolt® 2 anchors are permitted for use with fire-resistance-rated construction provided that at least one of the following conditions is fulfilled:
 - Anchors are used to resist wind or seismic forces only.
 - Anchors that support a fire-resistance-rated envelope or a fire-resistance-rated membrane, are protected by approved fire-resistance-rated materials, or have been evaluated for resistance to fire exposure in accordance with recognized standards.
 - Anchors are used to support nonstructural elements.
- 5.18 Use of zinc-plated carbon steel anchors is limited to dry, interior locations.
- 5.19 Periodic special inspection must be provided in accordance with Section 4.4 of this report.
- 5.20 The anchors are manufactured by Simpson Strong-Tie Company Inc., under an approved quality-control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

Data in accordance with the [ICC-ES Acceptance Criteria for Mechanical Anchors in Concrete Elements \(AC193\)](#), dated October 2017 (editorially revised December 2020), including optional suitability tests for seismic tension and shear; profile steel deck soffit tests; and quality control documentation.

7.0 IDENTIFICATION

- 7.1 The Strong-Bolt® 2 anchors are identified in the field by dimensional characteristics, head stamp, material specifications and packaging. The Strong-Bolt® 2 anchor has the Simpson Strong-Tie Company Inc., No Equal logo ≠ stamped on the expansion clip, and a length identification code embossed on the exposed threaded end. Table 6 shows the length identification codes. The packaging label bears the manufacturer's name and contact information, anchor name, anchor size and length, quantity, and the evaluation report number (ESR-3037).

7.2 The report holder's contact information is the following:

SIMPSON STRONG-TIE COMPANY INC.
5956 WEST LAS POSITAS BOULEVARD
PLEASANTON, CALIFORNIA 94588
(800) 999-5099
www.strongtie.com



FIGURE 1—STRONG-BOLT® 2 WEDGE ANCHOR (CARBON STEEL VERSION)




FIGURE 2—STRONG-BOLT® 2 WEDGE ANCHOR INSTALLATION




FIGURE 3—STRONG-BOLT® 2 WEDGE ANCHOR INSTALLATION SEQUENCE




FIGURE 4—INTERPOLATION OF MINIMUM EDGE DISTANCE AND ANCHOR SPACING¹

¹Interpolation only valid for 1/2-, 5/8- and 3/4- inch diameter carbon steel and 3/8-, 1/2- and 5/8-inch-diameter stainless-steel anchors. Spacing and edge distance combinations must fall on or above and to the right of the diagonal line.

TABLE 1A—CARBON STEEL STRONG-BOLT® 2 ANCHOR INSTALLATION INFORMATION¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR SIZE												
			Carbon Steel												
			1/4 inch ⁴	3/8 inch ⁵	1/2 inch ⁵		5/8 inch ⁵		3/4 inch ⁵		1 inch ⁵				
Installation Information															
Nominal Diameter	d_a	in.	1/4	3/8	1/2		5/8		3/4		1				
Drill Bit Diameter	d	in.	1/4	3/8	1/2		5/8		3/4		1				
Baseplate Clearance Hole Diameter ²	d_c	in.	5/16	7/16	9/16		11/16		7/8		1 1/8				
		(mm)	(7.9)	(11.1)	(14.3)		(17.5)		(22.2)		(28.6)				
Installation Torque	T_{inst}	ft-lbf	4	30	60		90		150		230				
		(N-m)	(5.4)	(40.7)	(81.3)		(122.0)		(203.4)		(311.9)				
Nominal Embedment Depth	h_{nom}	in.	1 3/4	1 7/8	2 1/8	2 3/4	3 7/8	3 3/8	5 1/8	4 1/8	5 3/4	5 1/4	9 3/4		
		(mm)	(45)	(48)	(73)	(70)	(98)	(86)	(130)	(105)	(146)	(133)	(248)		
Effective Embedment Depth	h_{ef}	in.	1 1/2	1 1/2	2 1/2	2 1/4	3 3/8	2 3/4	4 1/2	3 3/8	5	4 1/2	9		
		(mm)	(38)	(38)	(64)	(57)	(86)	(70)	(114)	(86)	(127)	(114)	(229)		
Minimum Hole Depth	h_{hole}	in.	1 7/8	2	3	3	4 1/8	3 5/8	5 3/8	4 3/8	6	5 1/2	10		
		(mm)	(48)	(51)	(76)	(76)	(105)	(92)	(137)	(111)	(152)	(140)	(254)		
Minimum Overall Anchor Length	l_{anch}	in.	2 1/4	2 3/4	3 1/2	3 3/4	5 1/2	4 1/2	6	5 1/2	7	7	13		
		(mm)	(57)	(70)	(89)	(95)	(140)	(114)	(152)	(140)	(178)	(178)	(330)		
Critical Edge Distance	c_{ac}	in.	2 1/2	6 1/2	6	6	7 1/2	7 1/2	9	6	8	18	13 1/2		
		(mm)	(64)	(165)	(152)	(152)	(191)	(191)	(229)	(152)	(203)	(457)	(343)		
Minimum Edge Distance	c_{min}	in.	1 3/4	6	6	4	4	6 1/2	6 1/2	6 1/2	4 1/4	4 1/4	8		
		(mm)	(45)	(152)	(152)	(102)	(102)	(165)	(165)	(165)	(108)	(108)	(203)		
	for $s \geq$	in.	-	-	6	4	4	-	5	5	10	10	-		
		(mm)	-	-	(152)	(102)	(102)	-	(127)	(127)	(254)	(254)	-		
Minimum Spacing	s_{min}	in.	2 1/4	3	2 3/4	2 3/4	2 3/4	5	2 3/4	2 3/4	3 1/2	3 1/2	8		
		(mm)	(57)	(76)	(70)	(70)	(70)	(127)	(70)	(70)	(89)	(89)	(203)		
	for $c \geq$	in.	-	-	12	12	12	-	8	8	6	6	-		
		(mm)	-	-	(305)	(305)	(305)	-	(203)	(203)	(152)	(152)	-		
Minimum Concrete Thickness	h_{min}	in.	3 1/4	3 1/4	4 1/2	4	5 1/2	6	5 1/2	6	7 7/8	6	8 3/4	9	13 1/2
		(mm)	(83)	(83)	(114)	(102)	(140)	(152)	(140)	(152)	(200)	(152)	(222)	(229)	(343)
Additional Data															
Specified Yield Strength	f_{ya}	psi	56,000	92,000	85,000				70,000		60,000				
		(MPa)	(386)	(634)	(586)				(483)		(414)				
Specified Tensile Strength	f_{uta}	psi	70,000	115,000						110,000		78,000			
		(MPa)	(483)	(793)						(758)		(538)			
Minimum Tensile and Shear Stress Area	A_{se}	in ²	0.0318	0.0514	0.105		0.166		0.270		0.472				
		(mm ²)	(21)	(33)	(68)		(107)		(174)		(305)				
Axial Stiffness in Service Load Range - Cracked and Uncracked Concrete ³	β	lb./in	73,700 ³	34,820	63,570		91,370		118,840		299,600				
		(N/mm)	(12,898) ₃	(6,098)	(11,133)		(16,001)		(20,812)		(52,468)				

For SI: 1 inch = 25.4 mm, 1 ft-lbf = 1.356 N-m, 1 psi = 6.89 Pa, 1 in² = 645 mm², 1 lbf/in = 0.175 N/mm.

¹The information presented in this table is to be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

²The clearance must comply with applicable code requirements for the connected element.

³The tabulated value of β for 1/4-inch-diameter carbon steel Strong-Bolt® 2 anchor is for installations in uncracked concrete only.

⁴The 1/4-inch-diameter (6.4 mm) anchor may be installed in top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flange meets the minimum thicknesses specified in this table.

⁵The 3/8-inch- through 1-inch-diameter (9.5 mm through 25.4 mm) anchors may be installed in topside of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flange meets the minimum thicknesses specified in this table, and Tables 5 for the 3/8-inch and 1/2-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 1B—STAINLESS STEEL STRONG-BOLT® 2 ANCHOR INSTALLATION INFORMATION¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR SIZE								
			Stainless Steel								
			¹ / ₄ inch ⁴	³ / ₈ inch ⁵	¹ / ₂ inch ⁵	⁵ / ₈ inch ⁵	³ / ₄ inch ⁵				
Installation Information											
Nominal Diameter	d_a	in.	¹ / ₄	³ / ₈	¹ / ₂	⁵ / ₈	³ / ₄				
Drill Bit Diameter	d	in.	¹ / ₄	³ / ₈	¹ / ₂	⁵ / ₈	³ / ₄				
Baseplate Clearance Hole Diameter ²	d_c	in. (mm)	⁵ / ₁₆ (7.9)	⁷ / ₁₆ (11.1)	⁹ / ₁₆ (14.3)	¹¹ / ₁₆ (17.5)	⁷ / ₈ (22.2)				
Installation Torque	T_{inst}	ft-lbf (N-m)	4 (5.4)	30 (40.7)	65 (88.1)	80 (108.5)	150 (203.4)				
Nominal Embedment Depth	h_{nom}	in. (mm)	¹ / ₄ (45)	¹ / ₈ (48)	² / ₈ (73)	² / ₄ (70)	³ / ₈ (98)	³ / ₈ (86)	⁵ / ₈ (130)	⁴ / ₈ (105)	⁵ / ₄ (146)
Effective Embedment Depth	h_{ef}	in. (mm)	¹ / ₂ (38)	¹ / ₂ (38)	² / ₂ (64)	² / ₄ (57)	³ / ₈ (86)	² / ₄ (70)	⁴ / ₂ (114)	³ / ₈ (86)	5 (127)
Minimum Hole Depth	h_{hole}	in. (mm)	¹ / ₈ (48)	2 (51)	3 (76)	3 (76)	⁴ / ₈ (105)	⁵ / ₈ (92)	⁵ / ₈ (137)	⁴ / ₈ (111)	6 (152)
Minimum Overall Anchor Length	l_{anch}	in. (mm)	² / ₄ (57)	² / ₄ (70)	³ / ₂ (89)	³ / ₄ (95)	⁵ / ₂ (140)	⁴ / ₂ (114)	6 (152)	⁵ / ₂ (140)	7 (178)
Critical Edge Distance	c_{ac}	in. (mm)	² / ₂ (64)	⁶ / ₂ (165)	⁸ / ₂ (216)	⁴ / ₂ (114)	7 (178)	⁷ / ₂ (191)	9 (229)	8 (203)	8 (203)
Minimum Edge Distance	c_{min}	in. (mm)	¹ / ₄ (45)	6 (152)	⁶ / ₂ (165)	5 (127)	4 (102)	4 (102)	4 (102)	6 (152)	
	for $s \geq$	in. (mm)	- -	10 (254)	- -	- -	8 (203)	8 (203)	8 (203)	- -	
Minimum Spacing	s_{min}	in. (mm)	² / ₄ (57)	3 (76)	8 (203)	⁵ / ₂ (140)	4 (102)	⁶ / ₄ (159)	⁶ / ₂ (165)		
	for $c \geq$	in. (mm)	- -	10 (254)	- -	- -	8 (203)	⁵ / ₂ (140)	- -		
Minimum Concrete Thickness	h_{min}	in. (mm)	³ / ₄ (83)	³ / ₄ (83)	⁴ / ₂ (114)	⁴ / ₂ (114)	6 (152)	⁵ / ₂ (140)	⁷ / ₈ (200)	⁶ / ₄ (172)	⁸ / ₄ (222)
Additional Data											
Specified Yield Strength	f_{ya}	psi (MPa)	96,000 (662)	80,000 (552)	92,000 (634)	82,000 (565)	68,000 (469)				
Specified Tensile Strength	f_{uta}	psi (MPa)	120,000 (827)	100,000 (689)	115,000 (793)	108,000 (745)	95,000 (655)				
Minimum Tensile and Shear Stress Area	A_{se}	in ² (mm ²)	0.0255 (16)	0.0514 (33)	0.105 (68)	0.166 (107)	0.270 (174)				
Axial Stiffness in Service Load Range - Cracked and Uncracked Concrete ³	β	lb./in (N/mm)	54,430 ³ (9,525) ³	29,150 (5,105)	54,900 (9,614)	61,270 (10,730)	154,290 (27,020)				

For **S1**: 1 inch = 25.4 mm, 1 ft-lbf = 1.356 N-m, 1 psi = 6.89 Pa, 1 in² = 645 mm², 1 lbf/in = 0.175 N/mm.

¹The information presented in this table is to be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

²The clearance must comply with applicable code requirements for the connected element.

³The tabulated value of β for ¹/₄-inch-diameter stainless steel Strong-Bolt® 2 anchor is for installations in uncracked concrete only.

⁴The ¹/₄-inch-diameter (6.4 mm) anchor may be installed in top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in this table.

⁵The ³/₈-inch- through ³/₄-inch-diameter (9.5 mm through 19.1 mm) anchors may be installed in top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in this table, and [Table 5](#) for the ³/₈-inch and ¹/₂-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 2A—CARBON STEEL STRONG-BOLT® 2 ANCHOR TENSION STRENGTH DESIGN DATA¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER										
			Carbon Steel										
			1/4 inch ⁷	3/8 inch ⁸	1/2 inch ⁸	5/8 inch ⁸	3/4 inch ⁸	1 inch ⁸					
Anchor Category	1,2 or 3	-	1								2		
Nominal Embedment Depth	h_{nom}	in. (mm)	1 ^{3/4} (45)	1 ^{7/8} (48)	2 ^{7/8} (73)	2 ^{3/4} (70)	3 ^{7/8} (98)	3 ^{3/8} (86)	5 ^{1/8} (130)	4 ^{1/8} (105)	5 ^{3/4} (146)	5 ^{1/4} (133)	9 ^{3/4} (248)
Steel Strength in Tension (ACI 318-19 17.6.1, ACI 318-14 Section 17.4.1 or ACI 318-11 Section D.5.1)													
Steel Strength in Tension	N_{sa}	lb (kN)	2,225 (9.9)	5,600 (24.9)	12,100 (53.8)	19,070 (84.8)	29,700 (132.1)	36,815 (163.8)					
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.75								0.65		
Concrete Breakout Strength in Tension (ACI 318-19 17.6.2, ACI 318-14 Section 17.4.2 or ACI 318-11 Section D.5.2)													
Effective Embedment Depth	h_{ef}	in. (mm)	1 ^{1/2} (38)	1 ^{1/2} (38)	2 ^{1/2} (64)	2 ^{1/4} (57)	3 ^{3/8} (86)	2 ^{3/4} (70)	4 ^{1/2} (114)	3 ^{3/8} (86)	5 (127)	4 ^{1/2} (114)	9 (229)
Critical Edge Distance	c_{ac}	in. (mm)	2 ^{1/2} (64)	6 ^{1/2} (165)	6 (152)	6 (152)	7 ^{1/2} (191)	7 ^{1/2} (191)	9 (229)	6 (152)	8 (203)	18 (457)	13 ^{1/2} (343)
Effectiveness Factor - Uncracked Concrete	k_{uncr}	-	24	24	24	24	24	24	24	24	24	24	24
Effectiveness Factor - Cracked Concrete	k_{cr}	-	See Note 6	17	17	17	17	17	17	17	17	17	17
Modification Factor	$\psi_{c,N}$	-	See Note 6	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00
Strength Reduction Factor - Concrete Breakout Failure ³	ϕ_{cb}	-	0.65								0.55		
Pull-Out Strength in Tension (ACI 318-19 17.6.3, ACI 318-14 17.4.3.1 or ACI 318-11 Section D.5.3)													
Pull-Out Strength Cracked Concrete ($f'_c = 2500$ psi)	$N_{p,cr}$	lb (kN)	See Note 6 -	1,300 ⁵ (5.8) ⁵	2,775 ⁵ (12.3) ⁵	N/A ⁴ -	4,985 ⁵ (22.2) ⁵	N/A ⁴ -	6,895 ⁵ (30.7) ⁵	N/A ⁴ -	8,500 ⁵ (37.8) ⁵	7,700 ⁵ (34.3) ⁵	11,185 ⁵ (49.8) ⁵
Pull-Out Strength Uncracked Concrete ($f'_c = 2500$ psi)	$N_{p,uncr}$	lb (kN)	N/A ⁴ -	N/A ⁴ -	3,340 ⁵ (14.9) ⁵	3,615 ⁵ (16.1) ⁵	5,255 ⁵ (23.4) ⁵	N/A ⁴ -	9,025 ⁵ (40.1) ⁵	7,115 ⁵ (31.6) ⁵	8,870 ⁵ (39.5) ⁵	8,360 ⁵ (37.2) ⁵	9,690 ⁵ (43.1) ⁵
Strength Reduction Factor - Pullout Failure ³	ϕ_p	-	0.65								0.55		
Tensile Strength for Seismic Applications (ACI 318-19 17.10.3, ACI 318-14 17.2.3.3 or ACI 318-11 Section D.3.3.3)													
Tension Resistance of Single Anchor for Seismic Loads ($f'_c = 2500$ psi)	$N_{p,eq}$	lb (kN)	See Note 6 -	1,300 ⁵ (5.8) ⁵	2,775 ⁵ (12.3) ⁵	N/A ⁴ -	4,985 ⁵ (22.2) ⁵	N/A ⁴ -	6,895 ⁵ (30.7) ⁵	N/A ⁴ -	8,500 ⁵ (37.8) ⁵	7,700 ⁵ (34.3) ⁵	11,185 ⁵ (49.8) ⁵
Strength Reduction Factor - Pullout Failure ³	ϕ_{eq}	-	0.65								0.55		

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹The information presented in this table must be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

²The 3/8-inch-, 1/2-inch-, 5/8-inch- and 3/4-inch-diameter carbon steel Strong-Bolt® 2 anchors are ductile steel elements as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable. The 1-inch-diameter carbon steel Strong-Bolt® 2 anchor is a brittle steel element as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable.

³The strength reduction factor applies when the load combinations from the IBC or ACI 318 are used and the requirements of ACI 318-19 17.5.3, ACI 318-14 17.3.3 or ACI 318-11 D.4.3, as applicable, are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate strength reduction factor must be determined in accordance with ACI 318-11 D.4.4.

⁴As described in Section 4.1.4 of this report, N/A (Not Applicable) denotes that pullout resistance does not need to be considered.

⁵The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 2,500 \text{ psi})^{0.5}$ or $(f'_c / 17.2 \text{ MPa})^{0.5}$.

⁶The 1/4-inch-diameter carbon steel Strong-Bolt® 2 anchor installation in cracked concrete is beyond the scope of this report.

⁷The 1/4-inch-diameter (6.4 mm) anchor may be installed in top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in Table 1A.

⁸The 3/8-inch- through 1-inch-diameter (9.5 mm through 25.4 mm) anchors may be installed in top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in Table 1A, and Table 5 for the 3/8-inch and 1/2-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 2B—STAINLESS STEEL STRONG-BOLT® 2 ANCHOR TENSION STRENGTH DESIGN DATA¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER								
			Stainless Steel								
			1/4 inch ⁹	3/8 inch ¹⁰	1/2 inch ¹⁰	5/8 inch ¹⁰	3/4 inch ¹⁰				
Anchor Category	1,2 or 3	-	1								
Nominal Embedment Depth	h_{nom}	in. (mm)	1 ^{3/4} (45)	1 ^{7/8} (48)	2 ^{7/8} (73)	2 ^{3/4} (70)	3 ^{7/8} (98)	3 ^{3/8} (86)	5 ^{1/8} (130)	4 ^{1/8} (105)	5 ^{3/4} (146)
Steel Strength in Tension (ACI 318-19 17.6.1, ACI 318-14 17.4.1 or ACI 318-11 Section D.5.1)											
Steel Strength in Tension	N_{sa}	lb (kN)	3,060 (13.6)	5,140 (22.9)	12,075 (53.7)	17,930 (79.8)	25,650 (114.1)				
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.75								
Concrete Breakout Strength in Tension (ACI 318-19 17.6.2, ACI 318-14 17.4.2 or ACI 318-11 Section D.5.2)											
Effective Embedment Depth	h_{ef}	in. (mm)	1 ^{1/2} (38)	1 ^{1/2} (38)	2 ^{1/2} (64)	2 ^{1/4} (57)	3 ^{3/8} (86)	2 ^{3/4} (70)	4 ^{1/2} (114)	3 ^{3/8} (86)	5 (127)
Critical Edge Distance	c_{ac}	in. (mm)	2 ^{1/2} (64)	6 ^{1/2} (165)	8 ^{1/2} (216)	4 ^{1/2} (114)	7 (178)	7 ^{1/2} (191)	9 (229)	8 (203)	8 (203)
Effectiveness Factor - Uncracked Concrete	k_{uncr}	-	24	24	24	24	24	24	24	24	24
Effectiveness Factor - Cracked Concrete	k_{cr}	-	See Note 8	17	17	17	17	17	17	17	17
Modification Factor	$\psi_{c,N}$	-	See Note 8	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00
Strength Reduction Factor - Concrete Breakout Failure ³	ϕ_{cb}	-	0.65								
Pull-Out Strength in Tension (ACI 318-19 17.6.3, ACI 318-14 17.4.3 or ACI 318-11 Section D.5.3)											
Pull-Out Strength Cracked Concrete ($f'_c = 2500$ psi)	$N_{p,cr}$	lb (kN)	See Note 8 -	1,720 ⁶ (7.7) ⁶	3,145 ⁶ (14.0) ⁶	2,560 ⁵ (11.4) ⁵	4,305 ⁵ (19.1) ⁵	N/A ⁴ -	6,545 ⁷ (29.1) ⁷	N/A ⁴ -	8,230 ⁵ (36.6) ⁵
Pullout Strength Uncracked Concrete ($f'_c = 2500$ psi)	$N_{p,uncr}$	lb (kN)	1,925 ⁷ (8.6) ⁷	N/A ⁴ -	4,770 ⁶ (21.2) ⁶	3,230 ⁵ (14.4) ⁵	4,495 ⁵ (20.0) ⁵	N/A ⁴ -	7,615 ⁵ (33.9) ⁵	7,725 ⁷ (34.4) ⁷	9,625 ⁷ (42.8) ⁷
Strength Reduction Factor - Pullout Failure ³	ϕ_p	-	0.65								
Tensile Strength for Seismic Applications (ACI 318-19 17.10.3, ACI 318 17.2.3.3 or ACI 318-11 Section D.3.3.3)											
Tension Resistance of Single Anchor for Seismic Loads ($f'_c = 2500$ psi)	$N_{p,eq}$	lb (kN)	See Note 8 -	1,720 ⁶ (7.7) ⁶	2,830 ⁶ (12.6) ⁶	2,560 ⁵ (11.4) ⁵	4,305 ⁵ (19.1) ⁵	N/A ⁴ -	6,545 ⁷ (29.1) ⁷	N/A ⁴ -	8,230 ⁵ (36.6) ⁵
Strength Reduction Factor - Pullout Failure ³	ϕ_{eq}	-	0.65								

For S1: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹The information presented in this table must be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

²The stainless steel Strong-Bolt® 2 anchors are ductile steel elements as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable.

³The strength reduction factor applies when the load combinations from the IBC or ACI 318 are used and the requirements of ACI 318-19 17.5.3, ACI 318-14 17.3.3 or ACI 318-11 D.4.3, as applicable, are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate strength reduction factor must be determined in accordance with ACI 318-11 D.4.4.

⁴As described in Section 4.1.4 of this report, N/A (Not Applicable) denotes that pullout resistance does not need to be considered.

⁵The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying by $(\frac{f'_c}{2,500\text{psi}})^{0.5}$ or $(\frac{f'_c}{17.2\text{MPa}})^{0.5}$.

⁶The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying by $(\frac{f'_c}{2,500\text{psi}})^{0.3}$ or $(\frac{f'_c}{17.2\text{MPa}})^{0.3}$.

⁷The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying by $(\frac{f'_c}{2,500\text{psi}})^{0.4}$ or $(\frac{f'_c}{17.2\text{MPa}})^{0.4}$.

⁸The 1/4-inch-diameter stainless steel Strong-Bolt® 2 anchor installation in cracked concrete is beyond the scope of this report.

⁹The 1/4-inch-diameter (6.4 mm) anchor may be installed in top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in Table 1B.

¹⁰The 3/8-inch- through 3/4-inch-diameter (9.5 mm through 19.1 mm) anchors may be installed in top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in Table 1B, and Table 5 for the 3/8-inch and 1/2-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 3A—CARBON STEEL STRONG-BOLT[®] 2 ANCHOR SHEAR STRENGTH DESIGN DATA¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER										
			Carbon Steel										
			¹ / ₄ inch ⁵	³ / ₈ inch ⁶	¹ / ₂ inch ⁶	⁵ / ₈ inch ⁶	³ / ₄ inch ⁶	1 inch ⁶					
Anchor Category	1,2 or 3	-	1									2	
Nominal Embedment Depth	h_{nom}	in. (mm)	1 ³ / ₄ (45)	1 ⁷ / ₈ (48)	2 ⁷ / ₈ (73)	2 ³ / ₄ (70)	3 ⁷ / ₈ (98)	3 ³ / ₈ (86)	5 ¹ / ₈ (130)	4 ¹ / ₈ (105)	5 ³ / ₄ (146)	5 ¹ / ₄ (133)	9 ³ / ₄ (248)
Steel Strength in Shear (ACI 318-19 17.7.1, ACI 318-14 17.5.1 or ACI 318-11 Section D.6.1)													
Shear Resistance of Steel	V_{sa}	lb (kN)	965 (4.3)	1,800 (8.0)	7,235 (32.2)	11,035 (49.1)	14,480 (64.4)	15,020 (66.8)					
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.65									0.60	
Concrete Breakout Strength in Shear (ACI 318-19 17.7.2, ACI 318-14 17.5.2 or ACI 318-11 Section D.6.2)													
Outside Diameter	d_a	in. (mm)	0.250 (6.4)	0.375 (9.5)	0.500 (12.7)	0.625 (15.9)	0.750 (19.1)	1.000 (25.4)					
Load Bearing Length of Anchor in Shear	l_e	in. (mm)	1.500 (38)	1.500 (38)	2.500 (64)	2.250 (57)	3.375 (86)	2.750 (70)	4.500 (114)	3.375 (86)	5.000 (127)	4.500 (114)	8.000 (203)
Strength Reduction Factor - Concrete Breakout Failure ³	ϕ_{cb}	-	0.70										
Concrete Pryout Strength in Shear (ACI 318-19 17.7.3, ACI 318-14 17.5.3 or ACI 318-11 Section D.6.3)													
Coefficient for Pryout Strength	k_{cp}	-	1.0	1.0	2.0	1.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Effective Embedment Depth	h_{ef}	in. (mm)	1 ¹ / ₂ (38)	1 ¹ / ₂ (38)	2 ¹ / ₂ (64)	2 ¹ / ₄ (57)	3 ³ / ₈ (86)	2 ³ / ₄ (70)	4 ¹ / ₂ (114)	3 ³ / ₈ (86)	5 (127)	4 ¹ / ₂ (114)	9 (229)
Strength Reduction Factor - Concrete Pryout Failure ³	ϕ_{cp}	-	0.70										
Steel Strength in Shear for Seismic Applications (ACI 318-19 17.10.3, ACI 318-14 17.2.3.3 or ACI 318-11 Section D.3.3.3)													
Shear Strength of Single Anchor for Seismic Loads ($f'_c = 2500$ psi)	$V_{sa,eq}$	lb (kN)	See Note 4 -	1,800 (8.0)	6,510 (29.0)	9,930 (44.2)	11,775 (52.4)	15,020 (66.8)					
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.65									0.60	

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹The information presented in this table must be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

²The ³/₈-inch-, ¹/₂-inch-, ⁵/₈-inch- and ³/₄-inch-diameter carbon steel Strong-Bolt[®] 2 anchors are ductile steel elements as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable. The 1-inch-diameter carbon steel Strong-Bolt[®] 2 anchor is a brittle steel element as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable.

³ The strength reduction factor applies when the load combinations from the IBC or ACI 318 are used and the requirements of ACI 318-19 17.5.3, ACI 318-14 17.3.3 or ACI 318-11 D.4.3, as applicable, are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate strength reduction factor must be determined in accordance with ACI 318-11 D.4.4.

⁴The ¹/₄-inch-diameter carbon steel Strong-Bolt[®] 2 anchor installation in cracked concrete is beyond the scope of this report.

⁵The ¹/₄-inch-diameter (6.4 mm) anchor may be installed in the top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Table 1A](#).

⁶The ³/₈-inch- through 1-inch-diameter (9.5 mm through 25.4 mm) anchors may be installed in the top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Table 1A](#), and [Table 5](#) for the ³/₈-inch and ¹/₂-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 3B—STAINLESS STEEL STRONG-BOLT® 2 ANCHOR SHEAR STRENGTH DESIGN DATA¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER								
			Stainless Steel								
			¹ / ₄ inch ⁵	³ / ₈ inch ⁶	¹ / ₂ inch ⁶	⁵ / ₈ inch ⁶	³ / ₄ inch ⁶				
Anchor Category	1,2 or 3	-	1								
Nominal Embedment Depth	h_{nom}	in. (mm)	¹ / ₄ (45)	¹ / ₈ (48)	² / ₈ (73)	² / ₄ (70)	³ / ₈ (98)	³ / ₈ (86)	⁵ / ₈ (130)	⁴ / ₈ (105)	⁵ / ₄ (146)
Steel Strength in Shear (ACI 318-19 17.7.1, ACI 318-14 17.5.1 or ACI 318-11 Section D.6.1)											
Shear Resistance of Steel	V_{sa}	lb (kN)	1,605 (7.1)	3,085 (13.7)	7,245 (32.2)	6,745 (30.0)	10,760 (47.9)	15,045 (66.9)			
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.65								
Concrete Breakout Strength in Shear (ACI 318-19 17.7.2, ACI 318-14 17.5.2 or ACI 318-11 Section D.6.2)											
Outside Diameter	d_a	in. (mm)	0.250 (6.4)	0.375 (9.5)	0.500 (12.7)	0.625 (15.9)	0.750 (19.1)				
Load Bearing Length of Anchor in Shear	ℓ_e	in. (mm)	1.500 (38)	1.500 (38)	2.500 (64)	2.250 (57)	3.375 (86)	2.750 (70)	4.500 (114)	3.375 (86)	5.000 (127)
Strength Reduction Factor - Concrete Breakout Failure ³	ϕ_{cb}	-	0.70								
Concrete Pryout Strength in Shear (ACI 318-19 17.7.3, ACI 318-14 17.5.3 or ACI 318-11 Section D.6.3)											
Coefficient for Pryout Strength	k_{cp}	-	1.0	1.0	2.0	1.0	2.0	2.0	2.0		
Effective Embedment Depth	h_{ef}	in. (mm)	¹ / ₂ (38)	¹ / ₂ (38)	² / ₂ (64)	² / ₄ (57)	³ / ₈ (86)	² / ₄ (70)	⁴ / ₂ (114)	³ / ₈ (86)	5 (127)
Strength Reduction Factor - Concrete Pryout Failure ³	ϕ_{cp}	-	0.70								
Steel Strength in Shear for Seismic Applications (ACI 318-19 17.10.3, ACI 318-14 17.2.3.3 or ACI 318-11 Section D.3.3.3)											
Shear Strength of Single Anchor for Seismic Loads ($f'_c = 2500$ psi)	$V_{sa,eq}$	lb (kN)	See Note 4 -	3,085 (13.7)	6,100 (27.1)	6,745 (30.0)	10,760 (47.9)	13,620 (60.6)			
Strength Reduction Factor - Steel Failure ^{2,3}	ϕ_{sa}	-	0.65								

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹The information presented in this table must be used in conjunction with the design criteria of ACI 318-19 Chapter 17, ACI 318-14 Chapter 17 or ACI 318-11 Appendix D.

²The stainless steel Strong-Bolt® 2 anchors are ductile steel elements as defined in ACI 318 (-19 and -14) 2.3 or ACI 318-11 D.1, as applicable.

³ The strength reduction factor applies when the load combinations from the IBC or ACI 318 are used and the requirements of ACI 318-19 17.5.3, ACI 318-14 17.3.3 or ACI 318-11 D.4.3, as applicable, are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate strength reduction factor must be determined in accordance with ACI 318-11 D.4.4.

⁴The ¹/₄-inch-diameter stainless steel Strong-Bolt® 2 anchor installation in cracked concrete is beyond the scope of this report.

⁵The ¹/₄-inch-diameter (6.4 mm) anchor may be installed in the top of uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Table 1B](#).

⁶The ³/₈-inch- through ³/₄-inch-diameter (9.5 mm through 19.1 mm) anchors may be installed in the top of cracked and uncracked normal-weight and sand-lightweight concrete over profile steel deck where concrete thickness above upper flute meets the minimum thicknesses specified in [Table 1B](#), and [Table 5](#) for the ³/₈-inch and ¹/₂-inch-diameter (9.5 mm and 12.7 mm) anchors.

TABLE 4A—CARBON STEEL STRONG-BOLT® 2 ANCHOR TENSION AND SHEAR STRENGTH DESIGN DATA FOR THE SOFFIT OF NORMAL-WEIGHT OR SAND-LIGHTWEIGHT CONCRETE OVER PROFILE STEEL DECK, FLOOR AND ROOF ASSEMBLIES^{1,2,6,8}

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER								
			Lower Flute				Upper Flute				
			3/8 inch		1/2 inch		5/8 inch		3/4 inch		
Nominal Embedment Depth	h_{nom}	in. (mm)	2 (51)	3 ³ / ₈ (86)	2 ³ / ₄ (70)	4 ¹ / ₂ (114)	3 ³ / ₈ (86)	5 ⁵ / ₈ (143)	4 ¹ / ₈ (105)	2 (51)	2 ³ / ₄ (70)
Effective Embedment Depth	h_{ef}	in. (mm)	1 ⁵ / ₈ (41)	3 (76)	2 ¹ / ₄ (57)	4 (102)	2 ³ / ₄ (70)	5 (127)	3 ³ / ₈ (86)	1 ⁵ / ₈ (41)	2 ¹ / ₄ (57)
Minimum Hole Depth	h_{hole}	in. (mm)	2 ¹ / ₈ (54)	3 ¹ / ₂ (89)	3 (76)	4 ³ / ₄ (121)	3 ⁵ / ₈ (92)	5 ⁷ / ₈ (149)	4 ³ / ₈ (111)	2 ¹ / ₈ (54)	3 (76)
Installation Torque	T_{inst}	ft-lbf (N-m)	30 (40.7)		60 (81.3)		90 (122.0)		150 (203.4)	30 (40.7)	60 (81.3)
Pullout Strength, concrete on metal deck (cracked) ³	$N_{p,deck,cr}$	lb (kN)	1,040 ⁷ (4.6) ⁷	2,615 ⁷ (11.6) ⁷	2,040 ⁷ (9.1) ⁷	3,645 ⁷ (16.2) ⁷	2,615 ⁷ (11.6) ⁷	4,990 ⁷ (22.2) ⁷	2,815 ⁷ (12.5) ⁷	1,340 ⁷ (6.0) ⁷	3,785 ⁷ (16.8) ⁷
Pullout Strength, concrete on metal deck (uncracked) ³	$N_{p,deck,uncr}$	lb (kN)	1,765 ⁷ (7.9) ⁷	3,150 ⁷ (14.0) ⁷	2,580 ⁷ (11.5) ⁷	3,840 ⁷ (17.1) ⁷	3,685 ⁷ (16.4) ⁷	6,565 ⁷ (29.2) ⁷	3,800 ⁷ (16.9) ⁷	2,275 ⁷ (10.1) ⁷	4,795 ⁷ (21.3) ⁷
Pullout Strength, concrete on metal deck (Seismic) ⁵	$N_{p,deck,eq}$	lb (kN)	1,040 ⁷ (4.6) ⁷	2,615 ⁷ (11.6) ⁷	2,040 ⁷ (9.1) ⁷	3,645 ⁷ (16.2) ⁷	2,615 ⁷ (11.6) ⁷	4,990 ⁷ (22.2) ⁷	2,815 ⁷ (12.5) ⁷	1,340 ⁷ (6.0) ⁷	3,785 ⁷ (16.8) ⁷
Steel Strength in Shear, concrete on metal deck ⁴	$V_{sa,deck}$	lb (kN)	1,595 (7.1)	3,490 (15.5)	2,135 (9.5)	4,580 (20.4)	2,640 (11.7)	7,000 (31.1)	4,535 (20.2)	3,545 (15.8)	5,920 (26.3)
Steel Strength in Shear, concrete on metal deck (Seismic) ⁵	$V_{sa,deck,eq}$	lb (kN)	1,595 (7.1)	3,490 (15.5)	1,920 (8.5)	4,120 (18.3)	2,375 (10.6)	6,300 (28.0)	3,690 (16.4)	3,545 (15.8)	5,330 (23.7)

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹Installation must comply with Section 4.3 and Figure 5.

²Profile steel deck must comply with Figure 5 and Section 3.3 of this report.

³The values must be used in accordance with Section 4.1.4 of this report.

⁴The values must be used in accordance with Section 4.1.5 of this report.

⁵The values must be used in accordance with Section 4.1.8 of this report.

⁶The minimum anchor spacing along the flute must be the greater of 3 h_{ef} or 1.5 times the flute width.

⁷The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 3,000\text{psi})^{0.5}$ or $(f'_c / 20.7\text{MPa})^{0.5}$.

⁸Concrete shall be normal-weight or sand-lightweight concrete having a minimum specified compressive strength, f'_c , of 3,000 psi (20.7 MPa).




FIGURE 5—INSTALLATION IN THE SOFFIT OF CONCRETE OVER PROFILE STEEL DECK FLOOR AND ROOF ASSEMBLIES¹

¹Anchors may be placed in the upper flute or lower flute of the steel deck assembly provided a minimum 1/2-inch concrete cover beyond the end of the anchor is provided. Anchors in the lower flute of Figure 5 may be installed with a maximum 1-inch offset in either direction from the centerline of the flute.

TABLE 4B—STAINLESS STEEL STRONG-BOLT[®] 2 ANCHOR TENSION AND SHEAR STRENGTH DESIGN DATA FOR THE SOFFIT OF NORMAL-WEIGHT OR SAND-LIGHTWEIGHT CONCRETE OVER PROFILE STEEL DECK, FLOOR AND ROOF ASSEMBLIES^{1,2,6,10}

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER								
			Lower Flute						Upper Flute		
			3/8 inch		1/2 inch		5/8 inch		3/4 inch	3/8 inch	1/2 inch
Nominal Embedment Depth	h_{nom}	in. (mm)	2 (51)	3 ^{3/8} (86)	2 ^{3/4} (70)	4 ^{1/2} (114)	3 ^{3/8} (86)	5 ^{5/8} (143)	4 ^{1/8} (105)	2 (51)	2 ^{3/4} (70)
Effective Embedment Depth	h_{ef}	in. (mm)	1 ^{5/8} (41)	3 (76)	2 ^{1/4} (57)	4 (102)	2 ^{3/4} (70)	5 (127)	3 ^{3/8} (86)	1 ^{5/8} (41)	2 ^{1/4} (57)
Minimum Hole Depth	h_{hole}	in. (mm)	2 ^{1/8} (54)	3 ^{1/2} (89)	3 (76)	4 ^{3/4} (121)	3 ^{5/8} (92)	5 ^{7/8} (149)	4 ^{3/8} (111)	2 ^{1/8} (54)	3 (76)
Installation Torque	T_{inst}	ft-lbf (N-m)	30 (40.7)		65 (88.1)		80 (108.5)		150 (203.4)	30 (40.7)	65 (88.1)
Pullout Strength, concrete on metal deck (cracked) ³	$N_{p,deck,cr}$	lb (kN)	1,230 ⁸ (5.5) ⁸	2,605 ⁸ (11.6) ⁸	1,990 ⁷ (8.9) ⁷	2,550 ⁷ (11.3) ⁷	1,750 ⁹ (7.8) ⁹	4,020 ⁹ (17.9) ⁹	3,030 ⁷ (13.5) ⁷	1,550 ⁸ (6.9) ⁸	2,055 ⁷ (9.1) ⁷
Pullout Strength, concrete on metal deck (uncracked) ³	$N_{p,deck,uncr}$	lb (kN)	1,580 ⁸ (7.0) ⁸	3,950 ⁸ (17.6) ⁸	2,475 ⁷ (11.0) ⁷	2,660 ⁷ (11.8) ⁷	2,470 ⁷ (11.0) ⁷	5,000 ⁷ (22.2) ⁷	4,275 ⁹ (19.0) ⁹	1,990 ⁸ (8.9) ⁸	2,560 ⁷ (11.4) ⁷
Pullout Strength, concrete on metal deck (seismic) ⁵	$N_{p,deck,eq}$	lb (kN)	1,230 ⁸ (5.5) ⁸	2,345 ⁸ (10.4) ⁸	1,990 ⁷ (8.9) ⁷	2,550 ⁷ (11.3) ⁷	1,750 ⁹ (7.8) ⁹	4,020 ⁹ (17.9) ⁹	3,030 ⁷ (13.5) ⁷	1,550 ⁸ (6.9) ⁸	2,055 ⁷ (9.1) ⁷
Steel Strength in Shear, concrete on metal deck ⁴	$V_{sa,deck}$	lb (kN)	2,285 (10.2)	3,085 (13.7)	3,430 (15.3)	4,680 (20.8)	3,235 (14.4)	5,430 (24.2)	6,135 (27.3)	3,085 (13.7)	5,955 (26.5)
Steel Strength in Shear, concrete on metal deck (seismic) ⁵	$V_{sa,deck,eq}$	lb (kN)	2,285 (10.2)	3,085 (13.7)	2,400 (10.7)	3,275 (14.6)	3,235 (14.4)	5,430 (24.2)	5,520 (24.6)	3,085 (13.7)	4,170 (18.5)

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹Installation must comply with Section 4.3 and Figure 5.

²Profile steel deck must comply with Figure 5 and Section 3.3 of this report.

³The values must be used in accordance with Section 4.1.4 of this report.

⁴The values must be used in accordance with Section 4.1.5 of this report.

⁵The values must be used in accordance with Section 4.1.8 of this report.

⁶The minimum anchor spacing along the flute must be the greater of $3h_{ef}$ or 1.5 times the flute width.

⁷The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 3,000 \text{ psi})^{0.5}$ or $(f'_c / 20.7 \text{ MPa})^{0.5}$.

⁸The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 3,000 \text{ psi})^{0.3}$ or $(f'_c / 20.7 \text{ MPa})^{0.3}$.

⁹The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 3,000 \text{ psi})^{0.4}$ or $(f'_c / 20.7 \text{ MPa})^{0.4}$.

¹⁰Concrete shall be normal-weight or sand-lightweight concrete having a minimum specified compressive strength, f'_c , of 3,000 psi (20.7 MPa).

TABLE 4C—CARBON STEEL STRONG-BOLT[®] 2 ANCHOR TENSION AND SHEAR STRENGTH DESIGN DATA FOR THE SOFFIT OF NORMAL-WEIGHT OR SAND-LIGHTWEIGHT CONCRETE OVER PROFILE STEEL DECK, FLOOR AND ROOF ASSEMBLIES^{1,2,6,8}

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL ANCHOR DIAMETER INSTALLED IN LOWER-FLUTE					
			³ / ₈ inch		¹ / ₂ inch		⁵ / ₈ inch	
Nominal Embedment Depth	h_{nom}	in. (mm)	2 (51)	³ / ₈ (86)	² / ₄ (70)	⁴ / ₂ (114)	³ / ₈ (86)	⁵ / ₈ (143)
Effective Embedment Depth	h_{ef}	in. (mm)	¹ / ₈ (41)	3 (76)	² / ₄ (57)	4 (102)	² / ₄ (70)	5 (127)
Minimum Hole Depth	h_{hole}	in. (mm)	² / ₈ (54)	³ / ₂ (89)	3 (76)	⁴ / ₄ (121)	⁵ / ₈ (92)	⁵ / ₈ (143)
Minimum Concrete Thickness	$h_{min,deck}$	in. (mm)	2 (51)	2 (51)	2 (51)	³ / ₄ (83)	2 (51)	³ / ₄ (83)
Installation Torque	T_{inst}	ft-lbf (N-m)	30 (40.7)		60 (81.3)		90 (122)	
Pullout Strength, concrete on metal deck (cracked) ³	$N_{p,deck,cr}$	lb (kN)	1,295 ⁷ (5.8) ⁷	2,705 ⁷ (12.0) ⁷	2,585 ⁷ (11.5) ⁷	5,850 ⁷ (26.0) ⁷	3,015 ⁷ (13.4) ⁷	5,120 ⁷ (22.8) ⁷
Pullout Strength, concrete on metal deck (uncracked) ³	$N_{p,deck,uncr}$	lb (kN)	2,195 ⁷ (9.8) ⁷	3,260 ⁷ (14.5) ⁷	3,270 ⁷ (14.5) ⁷	6,165 ⁷ (27.4) ⁷	4,250 ⁷ (18.9) ⁷	6,735 ⁷ (30.0) ⁷
Pullout Strength, concrete on metal deck (seismic) ⁵	$N_{p,deck,eq}$	lb (kN)	1,295 ⁷ (5.8) ⁷	2,705 ⁷ (12.0) ⁷	2,585 ⁷ (11.5) ⁷	5,850 ⁷ (26.0) ⁷	3,015 ⁷ (13.4) ⁷	5,120 ⁷ (22.8) ⁷
Steel Strength in Shear, concrete on metal deck ⁴	$V_{sa,deck}$	lb (kN)	1,535 (6.8)	3,420 (15.2)	2,785 (12.4)	5,950 (26.5)	3,395 (15.1)	6,745 (30.0)
Steel Strength in Shear, concrete on metal deck (seismic) ⁵	$V_{sa,deck,eq}$	lb (kN)	1,535 (6.8)	3,420 (15.2)	2,505 (11.1)	5,350 (23.8)	3,055 (13.6)	6,070 (27.0)

For SI: 1 inch = 25.4 mm, 1 lbf = 4.45 N.

¹Installation must comply with Section 4.3 and Figure 6.

²Profile steel deck must comply with Figure 6 and Section 3.3 of this report.

³The values must be used in accordance with Section 4.1.4 of this report.

⁴The values must be used in accordance with Section 4.1.5 of this report.

⁵The values must be used in accordance with Section 4.1.8 of this report.

⁶The minimum anchor spacing along the flute must be the greater of $3h_{ef}$ or 1.5 times the flute width.

⁷The characteristic pull-out strength for greater concrete compressive strengths must be increased by multiplying the tabular value by $(f'_c / 3,000 \text{ psi})^{0.5}$ or $(f'_c / 20.7 \text{ MPa})^{0.5}$.

⁸Concrete shall be normal-weight or sand-lightweight concrete having a minimum specified compressive strength, f'_c of 3,000 psi (20.7 MPa).




FIGURE 6—INSTALLATION IN THE SOFFIT OF CONCRETE OVER PROFILE STEEL DECK FLOOR AND ROOF ASSEMBLIES¹

¹Anchors may be placed in the lower flute of the steel deck assembly provided a minimum ⁵/₈-inch concrete cover beyond the end of the anchor is provided. Anchors in the lower flute of Figure 6 may be installed with a maximum 1-inch offset in either direction from the centerline of the flute (1 in = 25.4 mm).

TABLE 5—CARBON STEEL AND STAINLESS STEEL STRONG-BOLT[®] 2 ANCHOR INSTALLATION INFORMATION IN THE TOPSIDE OF NORMAL-WEIGHT OR SAND-LIGHTWEIGHT CONCRETE-FILLED PROFILE STEEL DECK FLOOR AND ROOF ASSEMBLIES^{1,4,5}

Design Information	Symbol	Units	Nominal Anchor Diameter (inch)						
			Carbon Steel Strong-Bolt 2 ²			Stainless Steel Strong-Bolt 2 ³			
			³ / ₈	¹ / ₂	³ / ₈	¹ / ₂			
Nominal Embedment Depth	h_{nom}	in.	1 ⁷ / ₈	1 ⁷ / ₈	2 ³ / ₄	3 ⁷ / ₈	1 ⁷ / ₈	1 ⁷ / ₈	2 ³ / ₄
Effective Embedment Depth	h_{ef}	in.	1 ¹ / ₂	1 ¹ / ₂	2 ¹ / ₄	3 ³ / ₈	1 ¹ / ₂	1 ¹ / ₂	2 ¹ / ₄
Minimum Concrete Thickness ⁶	$h_{min,deck}$	in.	2 ¹ / ₂	3 ¹ / ₄	3 ¹ / ₄	4 ³ / ₁₆	2 ¹ / ₂	3 ¹ / ₄	3 ¹ / ₄
Critical Edge Distance	$C_{ac,deck,to p}$	in.	4 ³ / ₄	4	4	6	4 ³ / ₄	4	4
Minimum Edge Distance	$C_{min,deck,t op}$	in.	4 ³ / ₄	4 ¹ / ₂	4 ³ / ₄	12	4 ³ / ₄	4 ³ / ₄	6
Minimum Spacing	$S_{min,deck,t op}$	in.	7	6 ¹ / ₂	8	3 ¹ / ₂	6 ¹ / ₂	6 ¹ / ₂	8

For SI: 1 inch = 25.4mm, 1 lbf = 4.45N.

¹Installation must comply with Sections 4.1.6, 4.1.11 and 4.3 and Figure 7 of this report.

²Design capacity shall be based on calculations according to values in Tables 2A and 3A of this report.

³Design capacity shall be based on calculations according to values in Tables 2B and 3B of this report.

⁴Minimum flute depth (distance from top of flute to bottom of flute) is 1¹/₂ inch, see Figure 7.

⁵Steel deck thickness shall be minimum 20 gauge.

⁶Minimum concrete thickness ($h_{min,deck}$) refers to concrete thickness above upper flute, see Figure 7.




FIGURE 7—INSTALLATION ON THE TOP OF CONCRETE-FILLED PROFILE STEEL DECK FLOOR AND ROOF ASSEMBLIES

TABLE 6—LENGTH IDENTIFICATION HEAD MARKS ON STRONG-BOLT® 2 ANCHORS (CORRESPONDS TO LENGTH OF ANCHOR – INCHES)

Mark	Units	A	B	C	D	E	F	G	H	I	J	K	L	M
From	in	1½	2	2½	3	3½	4	4½	5	5½	6	6½	7	7½
Up To But Not Including	in	2	2½	3	3½	4	4½	5	5½	6	6½	7	7½	8

Mark	Units	N	O	P	Q	R	S	T	U	V	W	X	Y	Z
From	in	8	8½	9	9½	10	11	12	13	14	15	16	17	18
Up To But Not Including	in	8½	9	9½	10	11	12	13	14	15	16	17	18	19

DIVISION: 03 00 00—CONCRETE

Section: 03 16 00—Concrete Anchors

DIVISION: 05 00 00—METALS

Section: 05 05 19—Post-Installed Concrete Anchors

REPORT HOLDER:

SIMPSON STRONG-TIE COMPANY INC.

EVALUATION SUBJECT:

SIMPSON STRONG-TIE® STRONG-BOLT® 2 WEDGE ANCHOR FOR CRACKED AND UNCRACKED CONCRETE

1.0 REPORT PURPOSE AND SCOPE**Purpose:**

The purpose of this evaluation report supplement is to indicate that the Simpson Strong-Tie® Strong-Bolt® 2 Wedge Anchors for cracked and uncracked concrete, described in ICC-ES evaluation report [ESR-3037](#), have also been evaluated for compliance with the codes noted below as adopted by the Los Angeles Department of Building and Safety (LADBS).

Applicable code editions:

- 2023 *City of Los Angeles Building Code* (LABC)
- 2023 *City of Los Angeles Residential Code* (LARC)

2.0 CONCLUSIONS

The Simpson Strong-Tie® Strong-Bolt® 2 Wedge Anchors for cracked and uncracked concrete, described in Sections 2.0 through 7.0 of the evaluation report [ESR-3037](#), comply with LABC Chapter 19, and the LARC, and are subjected to the conditions of use described in this supplement.

3.0 CONDITIONS OF USE

The Simpson Strong-Tie® Strong-Bolt® 2 Wedge Anchors described in this evaluation report supplement must comply with all of the following conditions:

- All applicable sections in the evaluation report [ESR-3037](#).
- The design, installation, conditions of use and identification of the anchors are in accordance with the 2021 *International Building Code*® (IBC) provisions noted in the evaluation report [ESR-3037](#).
- The design, installation and inspection are in accordance with additional requirements of LABC Chapters 16, 17 and City of Los Angeles Information Bulletin P/BC 2020-092, as applicable.
- Under the LARC, an engineered design in accordance with LARC Section R301.1.3 must be submitted.
- The allowable and design strength values listed in the evaluation report and tables are for the connection of the anchors to the concrete. The connection between the anchors and the connected members shall be checked for capacity (which may govern).
- For use in wall anchorage assemblies to flexible diaphragm applications, anchors shall be designed per the requirements of City of Los Angeles Information Bulletin P/BC 2020-071.

This supplement expires concurrently with the evaluation report, reissued August 2024.

DIVISION: 03 00 00—CONCRETE
Section: 03 16 00—Concrete Anchors

DIVISION: 05 00 00—METALS
Section: 05 05 19—Post-Installed Concrete Anchors

REPORT HOLDER:

SIMPSON STRONG-TIE COMPANY INC.

EVALUATION SUBJECT:

SIMPSON STRONG-TIE® STRONG-BOLT® 2 WEDGE ANCHOR FOR CRACKED AND UNCRACKED CONCRETE

1.0 REPORT PURPOSE AND SCOPE**Purpose:**

The purpose of this evaluation report supplement is to indicate that the Simpson Strong-Tie® Strong-Bolt® 2, described in ICC-ES evaluation report ESR-3037, has also been evaluated for compliance with the codes noted below.

Applicable code editions:

- 2023 Florida Building Code—Building
- 2023 Florida Building Code—Residential

2.0 CONCLUSIONS

The Simpson Strong-Tie® Strong-Bolt® 2, described in Sections 2.0 through 7.0 of ICC-ES evaluation report ESR-3037, complies with the *Florida Building Code—Building* or the *Florida Building Code—Residential*. The design requirements must be determined in accordance with the *Florida Building Code—Building* or the *Florida Building Code—Residential*, as applicable. The installation requirements noted in ICC-ES evaluation report ESR-3037 for the 2021 *International Building Code*® meet the requirements of the *Florida Building Code—Building* or the *Florida Building Code—Residential*, as applicable.

Use of the Simpson Strong-Tie® Strong-Bolt® 2, has also been found to be in compliance with the High-Velocity Hurricane Zone provisions of the *Florida Building Code—Building* or the *Florida Building Code—Residential* with the following conditions:

- a) For anchorage to wood members, the connection subject to uplift must be designed for no less than 700 pounds (3114 N).
- b) For connection to aluminum members, all expansion anchors must be installed no less than 3 inches (76 mm) from the edge of concrete slab and/or footings. All expansion anchors shall develop an ultimate withdrawal resisting force equal to four times the imposed load, with no stress increase for duration of load.

For products falling under Florida Rule 61G20-3, verification that the report holder's quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission for the type of inspections being conducted is the responsibility of an approved validation entity (or the code official when the report holder does not possess an approval by the Commission).

This supplement expires concurrently with the evaluation report, reissued August 2024.